



This is the accepted manuscript made available via CHORUS. The article has been published as:

Anomalous magnetothermoelectric behavior in massive Dirac materials

Yanan Li, Huichao Wang, Jingyue Wang, Chunming Wang, Yanzhao Liu, Jun Ge, Jingjing Niu, Wenjie Zhang, Pinyuan Wang, Ran Bi, Jinglei Zhang, Ji-Yan Dai, Jiaqiang Yan, David Mandrus, Nitin Samarth, Haizhou Lu, Xiaosong Wu, and Jian Wang

Phys. Rev. B **107**, 085140 — Published 23 February 2023

DOI: [10.1103/PhysRevB.107.085140](https://doi.org/10.1103/PhysRevB.107.085140)

Anomalous magneto-thermoelectric behavior in massive Dirac materials

Yanan Li^{1,10}, Huichao Wang², Jingyue Wang^{3,11}, Chunming Wang^{4,5}, Yanzhao Liu¹, Jun Ge¹, Jingjing Niu³, Wenjie Zhang³, Pinyuan Wang¹, Ran Bi³, Jinglei Zhang⁶, Ji-Yan Dai⁷, Jiaqiang Yan⁸, David Mandrus^{8,9}, Nitin Samarth¹⁰, Haizhou Lu^{5,16‡}, Xiaosong Wu^{3,15†}, Jian Wang^{1,5,12,13,14,17*}

¹*International Center for Quantum Materials, School of Physics, Peking University, Beijing 100871, China.*

²*School of Physics, Sun Yat-sen University, Guangzhou 510275, China.*

³*State Key Laboratory for Artificial Microstructure and Mesoscopic Physics, Peking University, Beijing 100871, China.*

⁴*Department of Physics, Shanghai Normal University, Shanghai 200234, China.*

⁵*Institute for Quantum Science and Engineering and Department of Physics, Southern University of Science and Technology, Shenzhen 518055, China.*

⁶*High Magnetic Field Laboratory, Chinese Academy of Sciences, Hefei 230031, Anhui, China.*

⁷*Department of Applied Physics, The Hong Kong Polytechnic University, Hung Hom, Kowloon, Hong Kong, China.*

⁸*Materials Science and Technology Division, Oak Ridge National Laboratory, Oak Ridge, Tennessee 37831, USA.*

⁹*Department of Materials Science and Engineering, University of Tennessee, Knoxville, Tennessee 37996, USA.*

¹⁰*Department of Physics, The Pennsylvania State University, University Park, PA 16802, USA.*

¹¹*Center for Nanochemistry, Beijing Science and Engineering Center for Nanocarbons, Beijing National Laboratory for Molecular Sciences, College of Chemistry and Molecular Engineering, Peking University, Beijing 100871, China.*

¹²*Collaborative Innovation Center of Quantum Matter, Beijing 100871, China.*

¹³*CAS Center for Excellence in Topological Quantum Computation, University of Chinese Academy of Sciences, Beijing 100190, China.*

¹⁴*Beijing Academy of Quantum Information Sciences, Beijing 100193, China.*

¹⁵*Beijing Key Laboratory of Quantum Devices, Peking University, Beijing 100871, China.*

¹⁶*Shenzhen Key Laboratory of Quantum Science and Engineering, Shenzhen 518055, China.*

¹⁷*Hefei National Laboratory, Hefei 230088, China.*

Extensive studies of electron transport in Dirac materials have shown positive magneto-resistance (MR) and positive magneto-thermopower (MTP) in a magnetic field perpendicular to the excitation current or thermal gradient. In contrast, measurements of electron transport often show a negative longitudinal MR and negative MTP for a magnetic field oriented along the excitation current or thermal gradient; this is attributed to the chiral anomaly in Dirac materials. Here,

we report a very different magneto-thermoelectric transport behavior in the massive Dirac material ZrTe₅. Although thin flakes show a commonly observed positive MR in a perpendicular magnetic field, distinct from other Dirac materials, we observe a sharp negative MTP. In a parallel magnetic field, we still observe a negative longitudinal MR, however, a remarkable positive MTP is observed for the fields parallel to the thermal gradients. Our theoretical calculations suggest that this anomalous magneto-thermoelectric behavior can be attributed to the screened Coulomb scattering. This work demonstrates the significance of impurity scattering in the electron transport of topological materials and provides deep insight into the novel magneto-transport phenomena in Dirac materials.

I. INTRODUCTION

Electrical and thermoelectric transport studies of Dirac materials are gaining increasing attention as a powerful tool to reveal the underlying physics, including the scattering mechanism, band structure, and topology. The experimental studies of Dirac materials, such as the Dirac semimetal Cd₃As₂ [1], the Weyl semimetal GdPtBi [2], and the massive Dirac material Pb_{1-x}Sn_xSe [3], demonstrate that both the magneto-thermopower (MTP) and magneto-resistance (MR) increase with an increasing perpendicular magnetic field (B) [1-4], while decrease with an increasing parallel field owing to the chiral anomaly [1,2]. The classical magneto-electric conductivity under a perpendicular magnetic field is given by the Boltzmann-Drude model: $\sigma(B) = \frac{en\mu}{(1+\mu^2 B^2)}$. Here, n is the carrier density; μ is the mobility with $\mu = \tau/m$ where m is the effective mass and τ is the relaxation time. According to the Mott relation [5], the Seebeck coefficient can be written as $S = -\frac{\pi^2 k_B^2 T}{3e} \left(\frac{\partial \ln \sigma(E)}{\partial E} \right)_{E_F}$, where $-e$ is the electron charge, k_B is the Boltzmann constant, T is the temperature, σ is the electric conductivity and E_F is the Fermi level. Therefore, the detailed behavior of MTP with magnetic field (i.e. whether it increases or decreases with field) is affected by the energy dependence of the relaxation time, which depends on the impurity scattering in the system.

The fundamental understanding of impurity scattering in topological materials has been a subject of intense scientific interest. In topological insulators, impurities lead to intricate effects on both the bulk and surface properties. For example, they can modify the electrical transport [6] or induce nanoscale spatial fluctuations in the helicity of surface states [7]. In topological semimetals, the electrical conductivity can also be tuned by impurities, resulting in diverse magnetic field dependent behavior [8-13]. Recently, there has been growing interest in the thermoelectric properties of topological materials in the presence of different charge-impurity scattering mechanisms [14-19]. The thermoelectric behavior is dramatically influenced by the scattering potential and thus may reveal the nature of different scattering mechanisms in topological materials.

Amongst topological materials, the massive Dirac material ZrTe_5 [20-22] has been a very promising platform to explore novel quantum effects because of its small Fermi surface [23-26]. Usually, ZrTe_5 can reach the quantum limit at a low magnetic field, which enables the discovery of many exotic quantum phenomena, such as the $\log B$ periodic quantum oscillations [27-29], the three-dimensional quantum Hall effect [30], and quantized plateau in the thermoelectric Hall conductivity [31]. Additionally, experiments have also shown anomalous transport behaviors, such as a negative longitudinal MR [32], an anomalous Hall effect [33-35] and an unconventional Hall effect [36], implying the nontrivial topological band structure of ZrTe_5 .

In this work, we present experimental studies of combined magneto-electrical and magneto-thermoelectric transport in ZrTe_5 thin flakes with dominant hole carriers at low temperatures. The MR shows a magnetic field dependence that is qualitatively similar to that observed in other Dirac materials but the thermoelectric behavior shows a novel field dependence distinct from that seen in previous studies of Dirac materials. When the magnetic field is perpendicular to the thermal gradient, we observe a negative MTP that saturates in the high field regime. In addition, a positive MTP is detected when the magnetic field is parallel to the thermal gradient. Our theoretical analyses indicate that this distinct MTP behavior can be attributed to the dominant long-range screened Coulomb scattering in these crystals. Our observations are highly valuable for understanding the quantum transport phenomena in Dirac materials.

II. METHODS

ZrTe_5 flakes were exfoliated with the scotch tape and transferred onto SiO_2/Si substrates. Then they were spin-coated with photoresists. After that, standard electron beam lithography, development, and metal evaporation were carried out to generate the electrodes and on-chip heater. For devices used in thermoelectric transport measurements, Pd (6.5 nm)/Au (40 nm) was used for the heater, and Pd (6.5 nm)/Au (300 nm) was used for other electrodes.

The temperature difference throughout the sample can be measured by the fabricated Pd/Au thermometers on top of the two ends of the thin flakes. The heat is generated by the on-chip micro heater. In the device, two ends of the nanoflake are sandwiched between the substrate and gold films serving as thermometers (Fig. S1 and Fig. 1(b)). It is reasonable to believe that the substrate, nanoflake and gold film are in thermal equilibrium at these two locations. Therefore, the temperature of the thermometer is indeed the temperature of the sample and the substrate. The measured temperature difference across the nanoflake in this configuration is relatively accurate. During the experiment, we made sure that this temperature difference was always much smaller than the average temperature

of the flake. The thermopower can be considered as a constant across the sample and thus can be calculated by the thermoelectric voltage divided by the temperature difference. Under this condition, there is no need to take into account the actual temperature distribution between two thermometers. This setup is commonly used for measuring thermopower of mesoscopic samples, such as carbon nanotubes [37], graphene [38] and topological semimetals [39] and Ref. [1].

Most transport measurements were performed in a 14 T helium cryostat and a 9 T Quantum Design Physical Property Measurement System by using the lock-in method. The ultrahigh field measurements were conducted in a static magnetic field facility (33 T) at the High Magnetic Field Laboratory, Chinese Academy of Sciences at Hefei.

III. EXPERIMENTAL RESULTS

We carried out the magneto-transport measurements on ZrTe_5 thin flakes exfoliated from bulk crystals. Figure 1(a) shows the crystalline structure of ZrTe_5 . Individual layers are coupled via van der Waals interactions, stacking along the b axis. Our bulk ZrTe_5 crystals with a very low carrier density were grown by the Te-flux method as reported [40]. For transport measurements, we used electron beam lithography and electron beam evaporation to pattern electrodes on thin flakes. An excitation current I or a thermal gradient ∇T was applied along the a axis of ZrTe_5 crystals ($I//a$ or $\nabla T//a$) for electric and thermoelectric transport measurements, respectively. Figure 1(b) shows the schematic of the measurement configuration and Fig. S1(a) [41] is an optical microscopy image of a typical device. Figure 1(c) displays the ρ - T curves from 300 K to 2 K for samples with different thicknesses. The exfoliated thin flakes clearly show a resistivity peak anomaly at a temperature that increases with decreasing flake thickness, similar to that in ZrTe_5 grown by the iodine vapor transfer (IVT) method [42]. We note that the peak anomaly is absent in the parent bulk crystals down to 2 K (Fig. 1(c)) while it usually presents in the IVT-grown bulk samples [43]. Additionally, the peak anomaly in the IVT-grown samples is usually accompanied by a change in the dominant carrier type [40]. However, this does not occur in our flux-grown samples. The different transport characteristics are likely related to the density of Te vacancies [40,44], and the flux-grown crystals contain relatively fewer Te vacancies (Fig. S8) [37, 38]. Figure 1(d) is the temperature dependent thermopower of a bulk crystal. The positive thermopower of both the bulk and thin flake samples (Fig. S2 [41]) indicates the dominant carriers are holes over the temperature range 300 K to 2 K, consistent with the Hall measurements (Figs. S3, S4, and S5 [41]). To avoid possible quality decay, the flakes were freshly cleaved and stored in the Ar glove box before measurements.




FIG. 1. Temperature dependence of the resistivity and thermopower in ZrTe₅. (a) Crystal structure of ZrTe₅. (b) Schematic of the measurement configuration. Contacts 1, 2, 11, 12 and contacts 5, 6, 7, 8 are used to inject an excitation current or measure the temperature at the two ends of the sample. Contacts 2, 3, 4, 5, 9, 10 are used to measure the MR and Hall signals in a standard Hall-bar setup. Contacts 2 and 5 or contacts 11 and 8 are used to measure the thermoelectric voltage. Contact 13 and 14 are used to apply a voltage on the heater to generate a thermal gradient on the sample. (c) The resistivity vs. temperature curves of the ZrTe₅ bulk crystal and thin flakes with different thicknesses. (d) Temperature dependence of the thermopower of a ZrTe₅ bulk crystal.

The magneto-transport behavior of thin flakes of ZrTe₅ was then measured by applying a perpendicular external magnetic field ($B//b$). In the electrical transport measurements, the samples show a positive MR with a sublinear field dependence (Figs. 2(a) and 2(b)), consistent with the previous reports [23,32,45,46]. Surprisingly, the magneto-thermoelectric transport measurements show a negative MTP in all samples. As shown in Fig. 2(c), the thermopower decreases sharply with the applied magnetic field and eventually saturates at large fields. The negative and saturated MTP extends up to 33 T (Fig. 2(d)).




FIG. 2. Normalized MR (a-b) and MTP (c-d) in ZrTe₅ flake samples under perpendicular fields ($B//b$ axis). The MR is calculated as $MR=R(B)/R(0) \times 100\%$. The MTP decreases sharply at low fields and saturates at high magnetic fields.

As the magnetic field orientation is tilted from the perpendicular configuration ($B//b$ axis) to the current direction ($B//a$ axis), the positive MR is first suppressed and then flips to the negative MR, as shown in Figs. 3(a) and 3(b). This behavior is further confirmed in another sample (Fig. S6(a) [41]). The amplitude of the negative MR generally decreases with increasing temperature and vanishes at a temperature between 100 K and 150 K, as shown in Fig. 3(b). The negative MTP is also suppressed when the field orientation deviates from b axis, and a positive MTP is observed when the magnetic field is tilted to the temperature gradient direction (Figs. 3(c) and 3(d)). The flat trace at low fields when $\theta=90^\circ$ (Fig. 3(c)) may be due to the presence of a tiny misalignment angle in the measurement, i.e., the sharp negative MTP contribution from the perpendicular component offsets the positive MTP under the parallel field). In another sample (Fig. S7 of Supplemental Material [41]), we observe clear positive MTP under parallel fields in the whole field range. As shown in Fig. S7, negative MTP is observed at low fields while the MTP remains positive field dependence at high fields when the orientation of the magnetic field is 3° away from the in-plane direction ($\theta=87^\circ$). This demonstrates that slight misalignment in the measurements of parallel field configuration significantly influences the low-field MTP result but barely change the high-field behavior. The amplitude of the positive MTP also decreases gradually with increasing temperature and survives up to 100 K (Fig. 3(d)). The longitudinal

magneto-thermoelectric conductance of the material is calculated based on the formula $\alpha(B) = S(B)\sigma(B)$ and shown in Figs. 3(e, f). Here, $\alpha(B)$ denotes the magneto-thermoelectric conductance. Thus, in addition to the positive longitudinal magneto-conductance, we also unveil a positive longitudinal magneto-thermoelectric conductance with a similar temperature and angle dependence as the positive MTP.




FIG. 3. Negative MR and positive MTP in ZrTe_5 under parallel magnetic fields ($B//I$ or $B//\nabla T$). (a, c) Angle dependence of normalized MR and MTP of ZrTe_5 thin flakes near the parallel magnetic fields. (b, d) Temperature dependence of the normalized MR and MTP of ZrTe_5 thin flakes under parallel fields. (e, f) Angle dependence and temperature dependence of the magneto-thermoelectric conductance calculated by the formula $\alpha(B) = S(B)\sigma(B)$.

IV. THEORETICAL ANALYSIS AND DISCUSSION

Figures 2 and 3 show that we have detected rather anomalous magneto-thermoelectric behavior in the flux-grown ZrTe_5 . Recent studies of bulk crystals and flakes (a few hundred nanometers thick) have shown that ZrTe_5 is a massive Dirac material which holds three-dimensional massive Dirac fermions with nearly linear bulk band dispersion and a bandgap [21,47]. To interpret the results, we use the massive Dirac model which has been effectively used to describe ZrTe_5 in previous studies [21]. Previous magneto-infrared spectroscopy measurements suggest that the quantum limit of flux-grown ZrTe_5 bulk crystals and thin flakes is lower than 1 T [20,48]. In our measurements, the maximum magnetic field is 33 T and thus we focus on the quantum transport and scattering

mechanism beyond the quantum limit. In perpendicular magnetic fields, the longitudinal conductivity σ_{xx} from the zeroth Landau level is related to the relaxation times $\tau_{1s\lambda}$, which arises from the virtual scattering processes between the zeroth Landau band E_{0+} and the first Landau bands $E_{1s\lambda}$. σ_{xx} is then given by [49,50]

$$\sigma_{xx} \simeq \frac{\hbar e^2}{2\pi} \frac{1}{2\ell_B^2} \int_{-\infty}^{\infty} d\varepsilon \left[-\frac{\partial n_F(\varepsilon)}{\partial \varepsilon} \right] \sum_{s,\lambda,k_z} \left[\left(v_{0,1s\lambda}^x \right)^2 \frac{\frac{\hbar}{2\tau_{1s\lambda}}}{(\varepsilon - E_{1s\lambda})^2 + \left(\frac{\hbar}{2\tau_{1s\lambda}} \right)^2} \delta(\varepsilon - E_{0+}) \right]. \quad (1)$$

Here $\ell_B = \sqrt{\hbar/eB}$ is the magnetic length, $n_F(\varepsilon)$ is the Fermi distribution function. The velocity element $v_{0,1s\lambda}^x$ couples the zeroth band and bands $1s\lambda$. In perpendicular magnetic fields, we also need to consider the Hall conductivity. Then, the resistivity and the Seebeck coefficient are given by $\rho_{xx} = \sigma_{xx}/(\sigma_{xx}^2 + \sigma_{xy}^2)$ and

$$S_{xx} = \frac{\pi^2 k_B^2 T}{3e} \frac{1}{\sigma_{xx}^2 + \sigma_{xy}^2} \left(\sigma_{xx} \frac{\partial \sigma_{xx}}{\partial E_F} + \sigma_{xy} \frac{\partial \sigma_{xy}}{\partial E_F} \right). \quad (2)$$

The relaxation time $\tau_{1s\lambda}$ depends on the electron-impurity scattering and can be calculated in the Born approximation [49,50] as

$$\frac{\hbar}{\tau_{1s\lambda}} = \pi n_i \ell_B^2 \sum_{k'_z} \left(F_{k_z, k'_z}^{1s\lambda, 0} \right)^2 \sum_{\mathbf{q}} |u(\mathbf{q})|^2 q_{\perp}^2 e^{-\ell_B^2 q_{\perp}^2 / 2} \delta_{q_z, k_z - k'_z} \delta(\varepsilon - E_{0+}^{k'_z}) \quad (3)$$

Here, n_i is the impurity density, $F_{k_z, k'_z}^{1s\lambda, 0}$ is a form factor, $u(\mathbf{q})$ is the Fourier transformation of the scattering potential, $q_{\perp}^2 = q_x^2 + q_y^2$, and $E_{0+}^{k'_z} = \sqrt{v^2 (k'_z)^2 + (b_z - m)^2}$ is the energy dispersion of the lowest Landau band with v the Fermi velocity, b_z the Zeeman splitting energy, and m the gap.

It is known that the impurity scattering potential could strongly influence the thermoelectric transport behavior. We have examined two typical scattering potentials, the screened Coulomb potential induced by charged impurities and the Gaussian scattering potential induced by neutral impurities. Since the anomalous thermoelectric behavior is stronger at low temperature, scattering from phonons is excluded from our analyses. The screened Coulomb potential of charged impurities is $U(\mathbf{r}) \propto \sum_i e^{-\kappa|\mathbf{r}-\mathbf{R}_i|}/|\mathbf{r}-\mathbf{R}_i|$, while the random Gaussian scattering potential from the neutral impurities is $U(\mathbf{r}) \propto \sum_i e^{-|\mathbf{r}-\mathbf{R}_i|^2/2d^2}$. Here, $\mathbf{R}_i$ is the position of a randomly distributed impurity, $1/\kappa$ is the screening length for screened Coulomb potential, and d is the acting range of the impurity potential for Gaussian potential. Our calculations (Figs. 4(a) and (b)) reveal that both scatterings yield positive MR and negative MTP as observed in the experiments when the potentials are long-ranged, that is, $1/\kappa, d > \ell_B$ (see Pt. II of Supplemental Material for more details [41]).

In a parallel field, the conductivity is related to the diagonal element of the velocity and the vertex correction of the velocity element should be considered. After vertex correction, the relaxation time is corrected to the transport time [51,52], giving the following formula

$$\sigma_{xx} = \frac{e^2}{h} \frac{1}{2\pi\ell_B^2} \frac{v^2 k_F}{E_F} \left(\frac{\tau_{k_F}^{\text{tr}}}{\hbar} + \frac{\tau_{-k_F}^{\text{tr}}}{\hbar} \right). \quad (4)$$

The transport time at the Fermi energy E_F is given by

$$\frac{\hbar}{\tau_{\pm k_F}^{\text{tr}}} = \frac{2E_F}{v^2 k_F} n_i \cos^2 \left[\frac{1}{2} (\alpha_{k_F} - \alpha_{-k_F}) \right] \sum_{q_y, q_z} |u(\pm 2k_F, q_y, q_z)|^2 e^{-(q_y^2 + q_z^2)\ell_B^2/2}. \quad (5)$$

with $\alpha_{\pm k_F} = \mp \tan^{-1}[vk_F/(b_x + m)]$, k_F the Fermi wave vector, b_x the Zeeman energy. The resistivity is the inverse of the conductivity and the Seebeck response can be obtained through the Mott relation. The transport time strongly relies on the scattering potential, which results in various magnetic-field dependences for various scattering types. In particular, the resistivity due to the Gaussian potential at fixed carrier density is given by:

$$\rho_{xx} = \frac{h}{e^2} \frac{n_i u_0^2}{v^2} \frac{(b_x + m)^2}{4\pi^4 v^2 n^2 \ell_B^2 (2d^2 + \ell_B^2)} e^{-16\pi^4 n^2 \ell_B^4 d^2}. \quad (6)$$

Since b_x increases with the magnetic field, while ℓ_B decreases, ρ_{xx} always increases with the field for arbitrary acting ranges (Fig. 4(d)), conflicting with the experimental results. However, the screened Coulomb scattering potential can lead to positive MTP and negative MR regardless of screening length in parallel fields (Fig. 4(c) and Fig. S10 [41]), consistent with our observations. This parallel field case is completely distinct from the perpendicular one. In perpendicular magnetic field, the in-plane motion is quantized and the in-plane momentum is not a good quantum number. The velocity is off-diagonal. The conductivity relates to the higher-order off-diagonal velocity element, which leads to the virtual process going back and forth between the zeroth band and the nearest high band [49]. The conductivity is almost inversely proportional to the relaxation time. Further, the Hall conductivity also influences the magnetoresistance and the Seebeck coefficient in perpendicular field case. Combining the calculations and experimental results, we qualitatively attribute the observed anomalous MTP and MR phenomena to the transport behavior in the presence of long-range screened Coulomb potential. More details of the calculations are shown in the Supplemental Material [41].

In the quantum limit, all the electrons occupy the lowest Landau band. This band is affected by the external magnetic field. In contrast to the classical case, the transport time or the relaxation time of this one-band quantum system is strongly influenced by the magnetic field and the scattering potential. Therefore, the transport behavior in the quantum limit is very sensitive to the scattering mechanism. As shown by the calculations, impurity scattering strongly influences the relaxation time (perpendicular field configuration) or transport time (parallel field configuration) in massive Dirac materials, which determines the magneto-transport properties. In the ZrTe₅ samples grown by the IVT method, the MTP shows a nonmonotonic field dependence in perpendicular field and a negative field dependence in parallel field [53,54]. The difference in thermoelectric transport behavior between IVT-grown

ZrTe₅ and flux-grown ZrTe₅ may originate from the different impurity scattering potentials formed during the growth process. Furthermore, our results suggest a need for caution in interpreting a negative MR under a parallel magnetic field as the signature of a chiral anomaly in Dirac materials [1] or helicity transport in massive Dirac materials [55]. Our studies indicate that impurity scattering should also be taken into serious consideration in the understanding of the anomalous transport behaviors.




FIG. 4. MR and MTP calculated using the massive Dirac model and different scattering potentials. The MR and MTP are normalized with respect to the value at B_q (quantum limit). (a, c) The results calculated using the long-range screened Coulomb scattering. A negative MTP and a positive MR are obtained under the perpendicular field, while a positive MTP and a negative MR are obtained under the parallel field, consistent with the experimental observations. (b, d) The results calculated using the Gaussian scattering. The MR is positive for the parallel field case, contrary to the experimental observations.

V. CONCLUSION

In conclusion, we observed anomalous magneto-thermoelectric transport behavior in thin flakes of massive Dirac material ZrTe₅. We found a large negative MTP in a perpendicular field while the MTP was positive in a parallel field. The MTP behavior is distinct from the generally expected results in Dirac materials although the observed MR shows a field dependence consistent with previous reports. This exotic behavior can be qualitatively explained by the long-range screened Coulomb scattering potential in the quantum limit of a massive Dirac band structure. The combined angle-dependent electrical and thermoelectric transport studies presented in this work provide important new insights into quantum transport phenomena in topological materials.

We thank Xiaobin Qiang and Chuanying Xi for helpful discussions. J.W. acknowledges the National Key R&D Program of China (2018YFA0305604), Beijing Natural Science Foundation (Z180010), the National Natural Science Foundation of China (11888101), the Strategic Priority Research Program of Chinese Academy of Sciences (XDB28000000), the Innovation Program for Quantum Science and Technology (2021ZD0302400). X.W. acknowledges the support from the National Key Basic Research R&D Program of China (2020YFA0308800) and the National Natural Science Foundation of China (11774009, 12074009). H.L. acknowledges the National Natural Science Foundation of China (11925402), Guangdong province (2016ZT06D348, 2020KCXTD001), Shenzhen High-level Special Fund (G02206304, G02206404), and the Science, Technology and Innovation Commission of Shenzhen Municipality (ZDSYS20170303165926217, JCYJ20170412152620376, KYTDPT20181011104202253), and Center for Computational Science and Engineering of SUSTech. H.W. acknowledges the National Natural Science Foundation of China (21BAA01133, 12004441, 92165204), the Hundreds of Talents program of Sun Yat-sen University and the Fundamental Research Funds for the Central Universities (2021qntd27). C.W. acknowledges the National Natural Science Foundation of China (11974249) and the Natural Science Foundation of Shanghai (19ZR1437300). J.Y. and D.M. acknowledge the U.S. Department of Energy, Office of Science, Basic Energy Sciences, Materials Sciences and Engineering Division.

Y.L., H.W., Jingyue W and C.W. contributed equally to this work.

*Corresponding author.

jianwangphysics@pku.edu.cn (J.W.)

†Corresponding author.

xswu@pku.edu.cn (X.W.)

*Corresponding author.

luhz@sustech.edu.cn (H.L.)

References

- [1] Z. Jia, C. Li, X. Li, J. Shi, Z. Liao, D. Yu, and X. Wu, Nat. Commun. **7**, 13013 (2016).
- [2] M. Hirschberger, S. Kushwaha, Z. Wang, Q. Gibson, S. Liang, Carina A. Belvin, B. A. Bernevig, R. J. Cava, and N. P. Ong, Nat. Mater. **15**, 1161 (2016).

- [3] T. Liang, Q. Gibson, J. Xiong, M. Hirschberger, S. P. Koduvayur, R. J. Cava, and N. P. Ong, *Nat. Commun.* **4**, 2696 (2013).
- [4] B. Skinner and L. Fu, *Sci. Adv.* **4**, eaat2621 (2018).
- [5] J. M. Ziman, *Electrons and Phonons* Oxford Clarendon Press: Oxford, p500 (1960).
- [6] B. Skinner, T. Chen, and B. I. Shklovskii, *J. Exp. Theor. Phys.* **117**, 579 (2013).
- [7] H. Beidenkopf, P. Roushan, J. Seo, L. Gorman, I. Drozdov, Y. S. Hor, R. J. Cava, and A. Yazdani, *Nat. Phys.* **7**, 939 (2011).
- [8] B. Skinner, *Phys. Rev. B* **90**, 060202 (2014).
- [9] J. Klier, I. V. Gornyi, and A. D. Mirlin, *Phys. Rev. B* **92**, 205113 (2015).
- [10] S. Das Sarma, E. H. Hwang, and H. Min, *Phys. Rev. B* **91**, 035201 (2015).
- [11] D. A. Pesin, E. G. Mishchenko, and A. Levchenko, *Phys. Rev. B* **92**, 174202 (2015).
- [12] S. Das Sarma and E. H. Hwang, *Phys. Rev. B* **91**, 195104 (2015).
- [13] H.-Z. Lu and S.-Q. Shen, *Front. Phys.* **12**, 127201 (2017).
- [14] R. Takahashi and S. Murakami, *Semicond Sci Technol* **27**, 124005 (2012).
- [15] R. Lundgren, P. Laurell, and G. A. Fiete, *Phys. Rev. B* **90**, 165115 (2014).
- [16] Q. Chen and G. A. Fiete, *Phys. Rev. B* **93**, 155125 (2016).
- [17] A. Pariari, N. Khan, R. Singha, B. Satpati, and P. Mandal, *Phys. Rev. B* **94**, 165139 (2016).
- [18] V. Könye and M. Ogata, *Phys. Rev. B* **100**, 155430 (2019).
- [19] L. X. Fu and C. M. Wang, *Phys. Rev. B* **105**, 035201 (2022).
- [20] Y. Jiang, Z. L. Dun, H. D. Zhou, Z. Lu, K. W. Chen, S. Moon, T. Besara, T. M. Siegrist, R. E. Baumbach, D. Smirnov, and Z. Jiang, *Phys. Rev. B* **96**, 041101 (2017).
- [21] Z.-G. Chen, R. Y. Chen, R. D. Zhong, J. Schneeloch, C. Zhang, Y. Huang, F. Qu, R. Yu, Q. Li, G. D. Gu, and N. L. Wang, *Proc. Natl. Acad. Sci. U.S.A.* **114**, 816 (2017).
- [22] Y. Zhang, C. Wang, L. Yu, G. Liu, A. Liang, J. Huang, S. Nie, X. Sun, Y. Zhang, B. Shen, J. Liu, H. Weng, L. Zhao, G. Chen, X. Jia, C. Hu, Y. Ding, W. Zhao, Q. Gao, C. Li, S. He, L. Zhao, F. Zhang, S. Zhang, F. Yang, Z. Wang, Q. Peng, X. Dai, Z. Fang, Z. Xu, C. Chen, and X. J. Zhou, *Nat. Commun.* **8**, 15512 (2017).
- [23] Y. Liu, X. Yuan, C. Zhang, Z. Jin, A. Narayan, C. Luo, Z. Chen, L. Yang, J. Zou, X. Wu, S. Sanvito, Z. Xia, L. Li, Z. Wang, and F. Xiu, *Nat. Commun.* **7**, 12516 (2016).
- [24] X.-B. Li, W.-K. Huang, Y.-Y. Lv, K.-W. Zhang, C.-L. Yang, B.-B. Zhang, Y. B. Chen, S.-H. Yao, J. Zhou, M.-H. Lu, L. Sheng, S.-C. Li, J.-F. Jia, Q.-K. Xue, Y.-F. Chen, and D.-Y. Xing, *Phys. Rev. Lett.* **116**, 176803 (2016).
- [25] R. Wu, J. Z. Ma, S. M. Nie, L. X. Zhao, X. Huang, J. X. Yin, B. B. Fu, P. Richard, G. F. Chen, Z. Fang, X. Dai, H. M. Weng, T. Qian, H. Ding, and S. H. Pan, *Phys. Rev. X* **6**, 021017 (2016).
- [26] G. Manzoni, L. Gragnaniello, G. Autès, T. Kuhn, A. Sterzi, F. Cilento, M. Zacchigna, V. Enenkel, I. Vobornik, L. Barba, F. Bisti, P. Bugnon, A. Magrez, V. N. Strocov, H. Berger, O. V. Yazyev, M. Fonin, F. Parmigiani, and A. Crepaldi, *Phys. Rev. Lett.* **117**, 237601 (2016).
- [27] H. Wang, H. Liu, Y. Li, Y. Liu, J. Wang, J. Liu, J.-Y. Dai, Y. Wang, L. Li, J. Yan, D. Mandrus, X. C. Xie, and J. Wang, *Sci. Adv.* **4**, eaau5096 (2018).
- [28] H. Wang, Y. Liu, Y. Liu, C. Xi, J. Wang, J. Liu, Y. Wang, L. Li, S. P. Lau, M. Tian, J. Yan, D. Mandrus, J.-Y. Dai, H. Liu, X. Xie, and J. Wang, *Natl. Sci. Rev.* **6**, 914 (2019).
- [29] Y. Liu, H. Wang, H. Zhu, Y. Li, J. Ge, J. Wang, L. Li, J.-Y. Dai, J. Yan, D. Mandrus, R. Joynt, and J. Wang, *npj Quantum Mater.* **5**, 88 (2020).
- [30] F. Tang, Y. Ren, P. Wang, R. Zhong, J. Schneeloch, S. A. Yang, K. Yang, P. A. Lee, G. Gu, Z. Qiao, and L. Zhang, *Nature* **569**, 537 (2019).
- [31] W. Zhang, P. Wang, B. Skinner, R. Bi, V. Kozii, C.-W. Cho, R. Zhong, J. Schneeloch, D. Yu, G. Gu, L. Fu, X. Wu,

- and L. Zhang, Nat. Commun. **11**, 1046 (2020).
- [32] Q. Li, D. E. Kharzeev, C. Zhang, Y. Huang, I. Pletikosić, A. V. Fedorov, R. D. Zhong, J. A. Schneeloch, G. D. Gu, and T. Valla, Nat. Phys. **12**, 550 (2016).
- [33] Z. Sun, Z. Cao, J. Cui, C. Zhu, D. Ma, H. Wang, W. Zhuo, Z. Cheng, Z. Wang, X. Wan, and X. Chen, npj Quantum Mater. **5**, 36 (2020).
- [34] T. Liang, J. Lin, Q. Gibson, S. Kushwaha, M. Liu, W. Wang, H. Xiong, J. A. Sobota, M. Hashimoto, P. S. Kirchmann, Z.-X. Shen, R. J. Cava, and N. P. Ong, Nat. Phys. **14**, 451 (2018).
- [35] M. Joshua, M. Xuetao, W. Chong, M. Paul, A.-S. Joss, J. Qianni, L. Zhaoyu, X. Di, Y. Matthew, and C. Jiun-Haw, arXiv: 2101.02681 (2021).
- [36] J. Ge, D. Ma, Y. Liu, H. Wang, Y. Li, J. Luo, T. Luo, Y. Xing, J. Yan, D. Mandrus, H. Liu, X. C. Xie, and J. Wang, Natl. Sci. Rev. **7**, 1879 (2020).
- [37] J. P. Small, K. M. Perez, and P. Kim, Phys. Rev. Lett. **91**, 256801 (2003).
- [38] Y. M. Zuev, W. Chang, and P. Kim, Phys. Rev. Lett. **102**, 096807 (2009).
- [39] J. Gooth, A. C. Niemann, T. Meng, A. G. Grushin, K. Landsteiner, B. Gotsmann, F. Menges, M. Schmidt, C. Shekhar, V. Süß, R. Hühne, B. Rellinghaus, C. Felser, B. Yan, and K. Nielsch, Nature **547**, 324 (2017).
- [40] P. Shahi, D. J. Singh, J. P. Sun, L. X. Zhao, G. F. Chen, Y. Y. Lv, J. Li, J. Q. Yan, D. G. Mandrus, and J. G. Cheng, Phys. Rev. X **8**, 021055 (2018).
- [41] *See Supplemental Material at URL for details, which includes Refs. [20,21,23,48-52,53-55].*
- [42] J. Niu, J. Wang, Z. He, C. Zhang, X. Li, T. Cai, X. Ma, S. Jia, D. Yu, and X. Wu, Phys. Rev. B **95**, 035420 (2017).
- [43] G. N. Kamm, D. J. Gillespie, A. C. Ehrlich, T. J. Wieting, and F. Levy, Phys. Rev. B **31**, 7617 (1985).
- [44] N. P. Ong and S. Liang, Nat. Rev. Phys. **3**, 394 (2021).
- [45] G. Zheng, J. Lu, X. Zhu, W. Ning, Y. Han, H. Zhang, J. Zhang, C. Xi, J. Yang, H. Du, K. Yang, Y. Zhang, and M. Tian, Phys. Rev. B **93**, 115414 (2016).
- [46] J. Wang, J. Niu, B. Yan, X. Li, R. Bi, Y. Yao, D. Yu, and X. Wu, Proc. Natl. Acad. Sci. U.S.A. **115**, 9145 (2018).
- [47] J. Mutch, W.-C. Chen, P. Went, T. Qian, I. Z. Wilson, A. Andreev, C.-C. Chen, and J.-H. Chu, Sci. Adv. **5**, eaav9771 (2019).
- [48] R. Y. Chen, Z. G. Chen, X. Y. Song, J. A. Schneeloch, G. D. Gu, F. Wang, and N. L. Wang, Phys. Rev. Lett. **115**, 176404 (2015).
- [49] H.-Z. Lu, S.-B. Zhang, and S.-Q. Shen, Phys. Rev. B **92**, 045203 (2015).
- [50] S.-B. Zhang, H.-Z. Lu, and S.-Q. Shen, New J. Phys. **18**, 053039 (2016).
- [51] H. Bruus and K. Flensberg, *Many-Body Quantum Theory in Condensed Matter Physics: An Introduction (Oxford Graduate Texts, 2004)*.
- [52] Y. Chen, H.-Z. Lu, and X. C. Xie, Phys. Rev. Lett. **121**, 036602 (2018).
- [53] W. Zhang, P. Wang, G. Gu, X. Wu, and L. Zhang, Phys. Rev. B **102**, 115147 (2020).
- [54] J. L. Zhang, C. M. Wang, C. Y. Guo, X. D. Zhu, Y. Zhang, J. Y. Yang, Y. Q. Wang, Z. Qu, L. Pi, H.-Z. Lu, and M. L. Tian, Phys. Rev. Lett. **123**, 196602 (2019).
- [55] A. V. Andreev and B. Z. Spivak, Phys. Rev. Lett. **120**, 026601 (2018).
- [56] A. A. Abrikosov, Phys. Rev. B **58**, 2788 (1998).
- [57] E. H. Hwang and S. Das Sarma, Phys. Rev. B **79**, 165404 (2009).
- [58] A. B. Pippard, *Magnetoresistance in Metals*, New York : Cambridge University Press (1989).