This is the accepted manuscript made available via CHORUS, the article has been published as:

Giant atomic displacement at a magnetic phase transition in metastable $\text{Mn}_{\{3\}}\text{O}_{\{4\}}$

S. Hirai, A. M. dos Santos, M. C. Shapiro, J. J. Molaison, N. Pradhan, M. Guthrie, C. A. Tulk,
I. R. Fisher, and W. L. Mao

Phys. Rev. B **87**, 014417 — Published 14 January 2013

DOI: [10.1103/PhysRevB.87.014417](https://doi.org/10.1103/PhysRevB.87.014417)

Giant atomic displacement at a magnetic phase transition in metastable Mn_3O_4

S. Hirai,^{1,2} A. M. dos Santos,³ M. C. Shapiro,^{2,4} J. J. Molaison,³ N. Pradhan,³ M. Guthrie,^{3,5} C. A. Tulk,³ I. R. Fisher,^{2,4} and W. L. Mao^{1,2}

¹*Department of Geological and Environmental Sciences, Stanford University, California 94305, USA*

²*Stanford Institute of Energy and Materials Science, SLAC National Accelerator Laboratory, 2575 Sand Hill Road, Menlo Park, CA 94025, USA*

³*Oak Ridge National Laboratory, 1 Bethel Valley Road, Oak Ridge, Tennessee 37831, USA*

⁴*Geballe Laboratory for Advanced Materials and Department of Applied Physics, Stanford University, Stanford, CA 94305, USA*

⁵*Carnegie Institution of Washington, 5251 Broadbranch Road, N.W., Washington, D.C. 20015, USA*

We present x-ray, neutron scattering and heat capacity data that reveal a coupled first-order magnetic and structural phase transition of the metastable mixed-valence post-spinel compound Mn_3O_4 at 210 K. Powder neutron diffraction measurements reveal a magnetic structure in which Mn^{3+} spins align antiferromagnetically along the edge-sharing a -axis, with a magnetic propagation vector $\mathbf{k} = [1/2, 0, 0]$. In contrast, the Mn^{2+} spins, which are geometrically frustrated, do not order until a much lower temperature. Although the Mn^{2+} spins do not directly participate in the magnetic phase transition at 210 K, structural refinements reveal a large atomic shift at this phase transition, corresponding to a physical motion of approximately 0.25 Å even though the crystal symmetry remains unchanged. This "giant" response is due to the coupled effect of built-in strain in the metastable post-spinel structure with the orbital realignment of the Mn^{3+} ion.

PACS numbers: 61.66.Fn, 61.05.fm, 75.47.Lx, 75.25.-j

I. INTRODUCTION

Large atomic movements can occur at displacive phase transitions. For example, atomic displacements of 0.05 - 0.4 Å are found for many ferroelectric materials, which lose their inversion symmetry¹. Typically, atomic displacements are much smaller for isostructural transitions, although it has recently been shown that a "giant" atomic displacement of 0.05 - 0.09 Å occurs in hexagonal manganites due to large magnetoelastic coupling². In the present work, we obtain a larger atomic displacement of 0.25 Å at a coupled magnetic and structural phase transition in metastable Mn_3O_4 post-spinel. Distinct from simple magnetostriction, this effect is a direct consequence of the highly strained metastable crystal lattice of Mn_3O_4 in the post-spinel structure. These results provide a new avenue for the design of materials exhibiting giant atomic displacements without breaking inversion symmetry.

Mn_3O_4 is a unique mixed-valence oxide which adopts a tetragonally distorted spinel structure at ambient conditions³. This spinel phase undergoes a structural phase transition at 15 GPa into the CaMn_2O_4 -type phase, referred to as post-spinel (Figure 1), which is quenchable to ambient pressure^{4,5}. The magnetic properties of Mn_3O_4 spinel have been extensively studied, with three magnetic transitions and a pronounced magnetodielectric coupling being reported^{6,7}. On the other hand, studies of Mn_3O_4 post-spinel are limited to structural work using X-ray diffraction (XRD)^{4,8} and Raman spectroscopy⁹. In the present work, we have determined the magnetic structure of Mn_3O_4 post-spinel at ambient pressure using neutron diffraction. We find that the onset of long range magnetic order of the Mn^{3+} moments at $T_N = 210$ K is coupled to a first order structural transition. The Mn^{2+} moments do not order at T_N due to the

FIG. 1: (color online) Crystal structure of metastable Mn_3O_4 post-spinel (orthorhombic, $Pbcm(57)$) at ambient pressure and room temperature. Gold shading represents the Mn^{2+}O_8 coordination polyhedra, while blue shading represents the Mn^{3+}O_6 octahedra. Large atomic displacements at the magnetic phase transition are a consequence of the built-in strain in this metastable structure.

intrinsic frustration of the crystal lattice, but nevertheless experience a large atomic shift of 0.25 Å. This "giant" effect is due to the exaggerated strain of the Mn^{2+}O_8 polyhedra in the metastable post-spinel structure.

II. EXPERIMENTAL METHODS

Polycrystalline samples of Mn_3O_4 post-spinel were synthesized using a Paris-Edinburgh cell apparatus. Mn_3O_4 spinel was used as a starting material, which was originally prepared by heating MnCO_3 in air at 1400 K for 16 hours. The starting material was pressurized up to

20 GPa using a cell fitted with polycrystalline diamond double toroidal anvils¹⁰, followed by a slow decompression at a rate of 5 GPa/hour to ambient pressure. The target pressure was set well above the transition pressure (15 GPa) in order to ensure full transformation of the starting material into the post-spinel phase.

Low temperature and room temperature neutron diffraction measurements were conducted at beamline 3 (SNAP) of the Spallation Neutron Source (SNS), Oak Ridge National Laboratory (ORNL) on the recovered sample at elevated temperatures between 290 K and 8 K in the d -spacing range of 0.5 - 6 Å. Detailed crystallographic information of Mn_3O_4 post-spinel obtained by Rietveld refinement of the crystal and magnetic structures are shown in Table I, Table II (at 60 K and 290 K). Since the atomic positions of octahedrally coordinated Mn^{3+} (d^4 : $t_{2g}^3 e_g^1$) and eight-fold coordinated Mn^{2+} (d^5 : $t_{2g}^3 e_g^2$) ions are crucial for determining the magnetic structure, we also confirmed the lattice parameters obtained from neutron diffraction using synchrotron XRD. Room temperature XRD data were collected at beamline 16-BMD of the Advanced Photon Source (APS) in Argonne National Laboratory (ANL) using x-rays with a wavelength of $\lambda = 0.41222$ Å. GSAS software was used for Rietveld refinement of the crystal and magnetic structures. Lattice constants obtained from the synchrotron XRD measurements were used as a starting model for the neutron diffraction refinement, while the atomic positions obtained from the neutron diffraction were used as a starting model for the XRD refinement, because neutron diffraction has better powder averaging (due to larger beam size) and more sensitive to the oxygen positions.

III. RESULTS AND DISCUSSION

Powder neutron diffraction and XRD refinement at room temperature (Figure 2(a)) demonstrate that the quenched sample of Mn_3O_4 crystallizes in the CaMn_2O_4 -type post-spinel structure with $Pbcm$ space group as anticipated following previous reports⁴. The lattice parameters obtained by these two methods were consistent, the difference being within the standard deviation. The room-temperature crystal structure, in which Mn^{3+}O_6 octahedra form one-dimensional edge-sharing chains along the a -axis, and zigzag along the b -axis, is shown in Figure 1. Eight-fold coordinated Mn^{2+} (d^5 : $t_{2g}^3 e_g^2$) ions are situated in the cavity provided by the zigzag connectivity of the Mn^{3+}O_6 octahedra. Detailed crystallographic data of atomic coordinates and bond lengths/angles are shown in Table I. In particular, we note that at room temperature, the Mn^{3+}O_6 octahedron comprises two short, two medium and two long $\text{Mn}^{3+}\text{-O}$ bond distances due to the anisotropic connectivity of the coordination-octahedra.

Powder neutron diffraction measurements at low temperature reveal a coupled magnetic and structural phase transition at $T_N = 210$ K. Magnetic peaks were found by

FIG. 2: (color online) Neutron powder diffraction profile of Mn_3O_4 post-spinel at (a) 290 K and (b) 60 K. Magnetic Bragg peaks are indicated by green marks, while nuclear Bragg peaks are indicated by black marks. The pink curve represents the difference between the observed and calculated neutron diffraction intensities based upon the refined magnetic structure described in the main text. (c) Magnetic structure for Mn^{3+} spins in Mn_3O_4 (arrows represent Mn^{3+} spins, black arrows are the spins parallel to the spin at the origin, while red arrows are the spins antiparallel to the spin at the origin). (d) Magnetic frustration of the Mn^{2+} spins against the antiferromagnetically ordered Mn^{3+} spins (black signs point out of the paper, while red signs point into the paper). The gold sphere represents the Mn^{2+} ion which is situated at the center of the honeycomb composed of six antiferromagnetically ordered Mn^{3+} spins.

excluding the nuclear peaks (< 3 Å), and the propagation vector of $\mathbf{k} = [1/2, 0, 0]$ for the magnetic unit cell was found to have the best fit using supercell in Fullprof software (representative data shown in Figure 2(b) for a temperature of 60 K). In other words, below 210 K, Mn_3O_4 post-spinel adopts an a -axis doubled magnetic unit cell (Figure 2(d)), in which Mn^{3+} spins are aligned antiferromagnetically along the edge sharing a -axis. Refinement was performed based on this magnetic unit cell in the $Pbca$ space group, yielding an ordered moment for the Mn^{3+} spins of $\mu_x = 3.49(2) \mu_B$ at 60 K (moment along the crystallographic a -axis). The temperature dependence of the ordered moment, shown in Figure 4(a), exhibits a rapid drop at $T_N = 210$ K, indicative of a first order phase transition. In contrast, as described in greater detail below, the Mn^{2+} moments do not appear to order at T_N , but remain paramagnetic down to approximately 50 K. Based on the refinement results described above, the temperature-dependence of the lattice parameters was also determined for a cooling cycle down

Parameters	60 K	290 K
a (Å)	3.032(1)	3.020(2)
b (Å)	9.842(6)	9.880(4)
c (Å)	9.568(4)	9.583(3)
V (Å ³)	284.4(1)	287.0(1)
Mn ³⁺ : x	0.308(8)	0.280(8)
Mn ³⁺ : y	0.114(2)	0.114(2)
Mn ³⁺ : z	0.070(3)	0.070(3)
Mn ³⁺ : U_{iso}	0.170(4)	0.106(7)
Mn ²⁺ : x	0.760(8)	0.876(4)
Mn ²⁺ : y	0.137(3)	0.137(3)
Mn ²⁺ : U_{iso}	0.018(5)	0.018(5)
O1: x	0.824(6)	0.824(4)
O1: U_{iso}	0.0064	0.0064
O2: x	0.332(4)	0.340(4)
O2: y	0.194(2)	0.194(2)
O2: U_{iso}	0.0064	0.0064
O3: x	0.800(2)	0.724(2)
O3: y	0.968(1)	0.968(1)
O3: z	0.105(2)	0.105(2)
O3: U_{iso}	0.0064	0.0064
R_{wp}	0.0246	0.0258

TABLE I: Table of crystallographic information of Mn₃O₄ post-spinel for representative temperatures above (290 K) and below (60 K) $T_N = 210$ K.

T (K)	Mn ³⁺ -O2-Mn ³⁺	O1-Mn ³⁺ -O1	O1-Mn ³⁺ -O2	O1-Mn ³⁺ -O3	O2-Mn ³⁺ -O3	O3-Mn ³⁺ -O3
290	129.7(3)	90.6(1)	86.6(1), 97.1(5)	84.5(3), 84.6(1), 92.5(6), 94.5(1)	91.8(5), 102.5(5)	76.2(3), 86.7(4), 90.8(1)
60	130.7(9)	90.4(1)	89.8(5), 92.7(6)	82.4(4), 88.0(5), 88.8(5), 96.7(3)	96.4(8), 99.2(6)	74.2(5), 88.7(6), 91.3(4)

TABLE II: Bond angles for representative temperatures above (290 K) and below (60 K) $T_N = 210$ K.

to 8 K. For the lattice constants a and b , a discontinuity around 210 K is clearly observed (Figure 3(a),(b)), signalling a coupled first order structural phase transition, which is accompanied by a lattice volume drop of 0.5(1) %. In spite of the considerable volume drop, this transition does not change the original $Pbcm$ symmetry and the material retains its inversion symmetry.

Heat capacity (C_p) measurements were made for similar polycrystalline samples of Mn₃O₄ post-spinel between 2 and 290 K, and representative data are shown in Figure 4(a). These measurements reveal a broad feature near 210 K, supporting the x-ray and neutron scattering evidence for a phase transition. The width of the "peak" in the heat capacity at this transition likely reflects the presence of inhomogeneous strain quenched from the high pressure synthesis. A similar broadening of an otherwise sharp first order transition has been observed for polycrystalline samples of other spinel compounds, such as MnV₂O₄¹¹.

Mn²⁺ ions occupy an inequivalent site to Mn³⁺ in the Mn₃O₄ crystal lattice. Consequently, any magnetic order associated with the Mn²⁺ ions must either lead to additional diffraction peaks for a $Q \neq 0$ structure, or an enhancement of the nuclear peaks for a $Q = 0$ structure. Neither effect is observed down to 55 K, and we conclude that the Mn²⁺ ions do not order until the lower temperature. This effect can be attributed to geometric frustra-

tion since the Mn²⁺ ions are situated at the center of a honeycomb arrangement of Mn³⁺ spins that are antiferromagnetically ordered (illustrated in Figure 2(e)). However, at 55 K an additional feature is seen in the heat capacity (Figure 4(a)), suggesting an additional phase transition. The crystal lattice does not change appreciably at this temperature, nor does the magnetic structure of the Mn³⁺ moments. However, neutron diffraction data reveal new broad and asymmetric magnetic peaks around 1.8 Å, 4.5 Å, 4.9 Å and 5.1 Å (Figure 2(c)). The d-spacing of these peaks is not consistent with the Mn³⁺ moments and indeed the T-dependence of the magnetic Bragg peaks associated with the Mn³⁺ sublattice evolve smoothly down to 8 K. The d-spacing of the additional magnetic peaks are, however, consistent with the ordering of the Mn²⁺ moments. Since these peaks are incommensurate with the nuclear Bragg peaks (Figure 2(c)) it appears that the Mn²⁺ moments adopt an incommensurate finite Q magnetic structure. However, the broad and asymmetric character of these peaks also implies that the associated correlation length is not especially long, and hence might be better characterized as short-range order.

The paramagnetic behavior of Mn²⁺ spins above 55 K is evident from susceptibility measurements (Figure 6). In comparison to CaMn₂O₄, for which the susceptibility monotonically decreases as the temperature is reduced below T_N , Mn₃O₄ reveals a susceptibility that increases

FIG. 3: Temperature dependence of lattice constants (a) a , (b) b , (c) c and (d) unit cell volume for Mn_3O_4 post-spinel. Vertical lines at 210 K indicate the coupled magnetic and structural phase transition.

upon cooling (upper inset to Figure 6). The data can be fit to the sum of a temperature-independent term and a Curie-Weiss term (i.e. $\frac{1}{\chi} = (\chi_0 + \frac{C}{T-\theta})^{-1}$) yielding an effective moment $\mu_{eff} = 2.32(2) \mu_B$ per formula unit in the temperature range between 100 and 200 K. This value should be treated with a certain amount of caution. The ordered lattice of Mn^{3+} moments will not

FIG. 4: (color online) Temperature dependence of (a) the magnetic moment of Mn^{3+} (left axis), the specific heat C_p (right axis); and (b) the atomic position of Mn^{2+} in Mn_3O_4 post-spinel, expressed on the left axis in terms of the atomic coordinate x in the unit cell, and on the right axis in terms of the actual atomic displacement relative to the position at 290 K. Dashed vertical line indicates approximate transition temperature. Inset shows the atomic displacements at 200 K found upon cooling below $T_N = 210$ K for Mn^{2+} (8 % shift in unit cell coordinates, corresponding to 0.25 Å) and O3 (5 % shift in unit cell coordinates, corresponding to 0.16 Å) represented by black arrows. The much smaller atomic displacement of Mn^{3+} (2 % shift in unit cell coordinates, corresponding to 0.06 Å) due to the magnetoelastic coupling is also shown. The directions of atomic displacement shown in the figure are only the representative ones, and equal number of atoms move in the opposite directions due to the $Pbcm$ symmetry. The arrows are illustrated in proportional length to the atomic displacements of Mn^{2+} , O3 and Mn^{3+} , but are all exaggerated by a factor of 4 for clarity.

give a temperature-independent susceptibility, and hence μ_{eff} does not provide a perfect measure of the actual effective moment of paramagnetic Mn^{2+} spins (for which one anticipates $\mu_{eff} = 5.92 \mu_B$).

At low temperatures, the susceptibility of Mn_3O_4 rises rapidly and exhibits a clear hysteresis between field cooled (FC) and zero-field cooled (ZFC) measurements, both of which are consistent with the onset of ferromagnetism. The magnetization (Figure 7) also exhibits a clear remnance for temperatures below $T_C \sim 55$ K. Evidently the incommensurate short-range magnetic order inferred from neutron diffraction measurements has a ferromagnetic component. The magnetization does not saturate in fields up to 5 T, but since the measurements were made for polycrystalline samples we cannot comment on the origin of this effect.

FIG. 5: (color online) Schematic view of the edge-sharing Mn^{3+}O_6 octahedra along the a -axis at 60 K (below T_N) and at 290 K (above T_N). Blue shading represents the coordination octahedra, and red spheres represent the oxygen ions. The associated $d_{x^2-y^2}$ orbitals are shown in black. Above T_N , $d_{x^2-y^2}$ and $d_{3z^2-r^2}$ orbitals are mixed and d orbitals partially align along the longest bonds of the Mn^{3+}O_6 octahedron. The Mn^{3+}O_6 octahedra are less distorted in the xy plane below T_N . The associated change in the orbital character leads to an enhanced exchange interaction along the a -axis.

FIG. 6: Zero field-cooled (ZFC) and field-cooled (FC) magnetic susceptibility (M/H) curve for Mn_3O_4 post-spinel measured in a field of 100 Oe. Upper inset shows the comparison of the ZFC magnetic susceptibility for Mn_3O_4 post-spinel (represented by black squares) with that for CaMn_2O_4 (represented by open squares) in the temperature regime of $100 < T < 300$ K (for comparison, both samples are measured in a field of 2000 Oe). ZFC magnetic susceptibility for CaMn_2O_4 was taken from¹². Lower inset shows the inverse susceptibility between 100 K and 200 K for Mn_3O_4 post-spinel, which can be fitted using the equation $\frac{1}{\chi} = (\chi_0 + \frac{C}{T-\theta})^{-1}$, combining temperature-independent and Curie-Weiss terms ($\chi_0 = 0.00886(3) \text{ (emu mol}^{-1}\text{)}$, $C = 0.668(9) \text{ (emu K mol}^{-1}\text{)}$, $\theta = 24.2(8) \text{ (K)}$). The Curie constant C gives $\mu_{\text{eff}} = 2.32(2) \mu_B$.

The small changes in lattice parameter and unit cell volume at T_N mask some startlingly large atomic displacements within the unit cell. Atomic coordinates and the associated bond lengths and angles are shown in Table I for representative temperatures above (290 K) and

FIG. 7: (color online) Magnetic hysteresis loops measured at $T=20$ K (square), $T=50$ K (triangle) and $T=100$ K (circle) for Mn_3O_4 post-spinel. The inset shows the temperature dependence of the zero-field magnetization M_0 obtained by a 4th order polynomial extrapolation of the magnetization at high field.

below (60 K) T_N . Focussing first on the Mn^{3+}O_6 coordination octahedra, the structural transition involves a relatively large motion of the O3 oxygen ion, with a change of 5 % in the unit cell coordinate, corresponding to a displacement of 0.16 Å. This motion leads to a smaller distortion of the octahedron in the xy plane relative to the room temperature structure, such that at low temperatures the four coordinating oxygen ions in the xy plane form an almost perfect square (Figure 5). The corresponding change in the orbital character of the Mn^{3+} ion affects the magnitude of the exchange interaction between nearest neighbour Mn^{3+} ions, possibly providing the driving force for the O3 ionic motion.

Surprisingly, our refinements also reveal a very large atomic shift along the a -axis for the Mn^{2+} ions (Figure 4(b)) at T_N . The unit cell coordinate changes by 8 %, corresponding to a displacement of 0.25 Å, *even though these ions do not directly participate in the magnetic phase transition*. This effect is even larger than that found in giant magneto-elastic compounds such as hexagonal manganites (atomic displacement: 0.05 - 0.09 Å)². However, in the case of Mn_3O_4 the effect does not arise directly from magnetoelastic coupling, because the Mn^{2+} ions do not directly participate in the magnetic phase transition. The origin of this effect is intimately linked to the metastable nature of Mn_3O_4 in the post-spinel structure at ambient pressure, and in particular to the severely strained Mn^{2+}O_8 polyhedra. Mn_3O_4 post-spinel is isostructural with CaMn_2O_4 , which is thermodynamically stable, but the Mn^{2+} ion is much smaller than Ca^{2+} . As a result, the Mn^{2+}O_8 polyhedron is considerably stretched relative to the ideal bond lengths. This is borne out by the bond valence sum (BVS), which is 1.82,

smaller than the formal valence 2. The associated strain is rather severe, and can act to magnify the effects of more modest ionic displacements at the magnetic phase transition. Specifically, on cooling below T_N , the associated change in position of the O3 ions described above, would result in a further reduction of the BVS of the Mn^{2+} ions if they did not move. Indeed, if the Mn^{2+} ions did not move at T_N , the BVS would change from 1.83 to 1.73, far below the optimal value of 2 associated with the formal $2+$ valence. Consequently, in order to minimize the elastic energy, the Mn^{2+} ions experience a giant atomic displacement, recovering a low temperature BVS of 1.83, closer to the expected value. Such a large atomic shift of Mn^{2+} suggests that Mn_3O_4 post-spinel is at the edge of the phase boundary between the post-spinel and the spinel phase and is therefore highly susceptible to large atomic displacements.

FIG. 8: The comparison of specific heat (C_p) of Mn_3O_4 post-spinel (represented by black squares) with C_p of CaMn_2O_4 (represented by open squares) in the temperature regime of $0 < T < 300$ K. The specific heat data of CaMn_2O_4 was taken from¹². The ferromagnetic transition at $T_C \sim 55$ K associated with Mn^{2+} moments is indicated by an arrow. This transition is absent for CaMn_2O_4 .

Since Mn_3O_4 post-spinel is isostructural with CaMn_2O_4 , and the only chemical difference is that Ca^{2+} is replaced by Mn^{2+} , it is instructive to compare the physical properties of these two compounds. Mn_3O_4 exhibits an insulating behavior similar to CaMn_2O_4 ¹² with a very large resistivity. CaMn_2O_4 exhibits long-range antiferromagnetic order below $T_N = 217$ K¹², comparable to that of Mn_3O_4 , and also adopts the same magnetic structure as the Mn^{3+} spins for Mn_3O_4 . However, in contrast with Mn_3O_4 post-spinel, the magnetic phase transition in CaMn_2O_4 is continuous and the associated atomic displacements of Ca^{2+} and O3 ions are considerably smaller (the corresponding differences in atomic positions between 300 K and 20 K are just 0.012 Å for Ca^{2+} , and 0.003 Å for O3¹³, relative to 0.25 Å and 0.16

Å for Mn^{2+} and O3 ions in Mn_3O_4 post-spinel). The origin of this difference lies in the metastable nature of post-spinel Mn_3O_4 . CaMn_2O_4 is a thermodynamically stable phase, and the specific crystal lattice is a minimum of the free energy. The lattice is relatively stiff, and associated motion of O3 ions in response to the onset of long-range magnetic order is correspondingly small. However, the built-in strain associated with the metastable post-spinel structure adopted by Mn_3O_4 quenched from high-pressure leads to a softer crystal lattice, and hence an exaggerated response of both the O3 and Mn^{2+} ions to the onset of long-range magnetic order. Figure 8 shows the comparison of our heat capacity data of Mn_3O_4 post-spinel with the previously reported heat capacity of CaMn_2O_4 ¹². Apart from the peak broadening near 215 K due to the strain effect, the only significant difference is found at temperatures lower than 55 K due to the onset of magnetic ordering associated with the Mn^{2+} moments.

IV. CONCLUSION

In conclusion, Mn_3O_4 in the post-spinel structure at ambient pressure undergoes an isostructural coupled magnetic and structural phase transition at $T_N = 210$ K. The built-in strain associated with the metastable structure leads to a "giant" atomic displacement of the Mn^{2+} ions at T_N , even though they do not directly participate in the magnetic order due to the effects of geometric frustration. This novel effect illustrates an alternative avenue to achieve giant atomic displacements coupled to magnetic phase transitions.

V. ACKNOWLEDGEMENTS

This research is funded by the U.S. Department of Energy (DOE), Office of Basic Energy Sciences (BES). S.H., W.L.M., M.S. and I.R.F. are supported by the U.S. Department of Energy (DOE), Office of Basic Energy Sciences (BES), Division of Materials Sciences and Engineering, under Contact No. DE-AC02-76SF00515. M.G. is supported by EFree, an Energy Frontier Research Center funded by DOE-BES. Neutron diffraction experiments at the SNAP facility were supported by SNS and Center of Nanophase Materials Science of ORNL. XRD experiments were performed at HPCAT, APS, ANL. HPCAT is supported by CIW, CDAC, UNLV, and LLNL through funding from DOE-NNSA, DOE-BES, and NSF. APS is supported by DOE-BES, under Contract No. DE-AC02-06CH11357. We thank D. Ikuta and W. Yang for help with the XRD experiments.

-
- ¹ R.W. Wyckoff, *Crystal Structures* (Krieger Publishing, New York, 1986).
- ² S. Lee, A. Pirogov, M. Kang, K-H. Jang, M. Yonemura, T. Kamiyama, S-W. Cheong, F. Gozzo, N. Shin, H. Kimura, Y. Noda and J-G. Park, *Nature* **451**, 805 (2008).
- ³ G. Aminoff, *Z. Kristallogr.* **64**, 475 (1926).
- ⁴ E. Paris, C.R. Ross and H. Olijnyk, *Eur. J. Mineral.* **4**, 87 (1992).
- ⁵ M. Merlini, M. Hanfland, M. Gemmi, S. Huotari, L. Simonelli, P. Strobel, *Am. Mineral.* **95**, 200 (2010).
- ⁶ T. Suzuki and T. Katsufuji, *Phys. Rev. B* **77**, 220402 (2008).
- ⁷ R. Tackett, G. Lawes, B.C. Melot, M. Grossman, E.S. Tøberer and R. Seshadri, *Phys. Rev. B* **76**, 024409 (2007).
- ⁸ Y. Moritomo, Y. Ohishi, A. Kuriki, E. Nishibori, M. Takata and M. Sakata, *J. Phys. Soc. Jpn.* **72**, 765 (2003).
- ⁹ X-J. Liu, S. Xu, K. Kato and Y. Moritomo, *J. Phys. Soc. Jpn.* **71**, 2820 (2002).
- ¹⁰ S. Klotz, J.M. Besson, G. Hamel, R.J. Nelmes, J.S. Loveday, *Appl. Phys. Lett.* **66**, 1735 (1995).
- ¹¹ H.D.Zhou, J.Lu and C.R.Wiebe, *Phys. Rev. B* **76**, 174403 (2007).
- ¹² B.D.White, J.A.Souza, C.Chiorescu, J.J.Neumeier and J.L.Cohn, *Phys. Rev. B* **79**, 104427 (2009).
- ¹³ C. D. Ling, J. J. Neumeier and D. N. Argyriou, *J. Solid State Chem.* **160**, 167 (2001).