

CHCRUS

This is the accepted manuscript made available via CHORUS. The article has been published as:

Effect of interlayer coupling on the coexistence of antiferromagnetism and superconductivity in Fe pnictide superconductors: A study of Ca_{0.74(1)}La_{0.26(1)}(Fe_{1-x}Co_{x})As_{2} single crystals Shan Jiang, Lian Liu, Michael Schütt, Alannah M. Hallas, Bing Shen, Wei Tian, Eve Emmanouilidou, Aoshuang Shi, Graeme M. Luke, Yasutomo J. Uemura, Rafael M. Fernandes, and Ni Ni

> Phys. Rev. B **93**, 174513 — Published 23 May 2016 DOI: 10.1103/PhysRevB.93.174513

Coexistence of superconductivity and antiferromagnetism in $Ca_{0.74(1)}La_{0.26(1)}(Fe_{1-x}Co_x)As_2$ single crystals

Shan Jiang,¹ Lian Liu,² Michael Schütt,³ Alannah M. Hallas,⁴ Bing Shen,¹ Wei Tian,⁵ Eve Emmanouilidou,⁶

Aoshuang Shi,⁶ Graeme M. Luke,⁴ Yasutomo J. Uemura,² Rafael. M. Fernandes,³ and Ni Ni^{1, *}

¹Department of Physics and Astronomy and California NanoSystems Institute,

University of California, Los Angeles, CA 90095, USA

²Department of Physics, Columbia University, New York, NY 10027, USA

³School of Physics and Astronomy, University of Minnesota, Minneapolis, MN 55455, USA

⁴Department of Physics, McMaster University, Hamilton, Ontario, L8S 4M1, Canada

⁵Quantum Condensed Matter Division, Oak Ridge National Laboratory, Oak Ridge, TK 37831, USA

⁶Department of Physics and Astronomy, University of California, Los Angeles, CA 90095, USA

We report the transport, thermodynamic, μ SR and neutron study of the Ca_{0.74(1)}La_{0.26(1)}(Fe_{1-x}Co_x)As₂ single crystals, mapping out the temperature-doping level phase diagram. Upon Co substitution on the Fe site, the structural/magnetic phase transitions in this 112 compound are suppressed and superconductivity up to 20 K occurs. Our measurements of the superconducting and magnetic volume fractions show that these two phases coexist microscopically in the underdoped region, in contrast to the related 10-3-8 Ca₁₀(Pt₃As₈)((Fe_{1-x}Pt_x)₂As₂)₅ compound, where coexistence is absent. Supported by model calculations, we discuss the differences in the phase diagrams of the 112 and 10-3-8 compounds in terms of the FeAs interlayer coupling, whose strength is affected by the character of the spacer layer, which is metallic in the 112 and insulating in the 10-3-8.

Since the observation of 26 K superconductivity (SC) in LaFeAsO_{1-x} F_x^1 , several families of Fe-based superconductors (FBS) have been discovered. Among them, $Ca_{1-x}La_xFeAs_2$ (CaLa112) with T_c up to 42 K, crystalizes in a monoclinic lattice^{2,3}. This crystal structure based on the FeAs-(Ca/La)-As-(Ca/La)-FeAs stacking contains the prototypical FeAs layers made of the edgesharing FeAs₄ tetrahedra, as well as As layers made of zig-zag chains. The presence of these As chains has made CaLa112 unique in many aspects. Our recent study shows the Ca_{0.73}La_{0.27}FeAs₂ compound, which has an effectively electron overdoped FeAs layer, is the "parent" compound of the CaLa112 FBS, highlighting the dual nature of itinerant and localized magnetism in FBS⁴. In this material, a monoclinic to triclinic structural phase transition occurs at 58 K and a paramagnetic to stripe antiferromagnetic (AFM) phase transition appears at 54 K. Furthermore, metallic spacer layers are observed via ARPES measurement^{4,5}. Besides Ca doping, which adds hole-like carriers, Co substitution on the Fe sites, which adds electron-like carriers, can also stabilize SC in Ca_{0.73}La_{0.27}FeAs₂^{4,6–8}. Therefore, as a FBS series with metallic spacer layers and no C_4 rotational symmetry, the characterization of the Co doped CaLa112 is of particular interest. Here we report a systematic study of Co doped $Ca_{0.73}La_{0.27}FeAs_2$ (Co-CaLa112). We show that upon Co doping, the structure/magnetic phase transitions in Ca_{0.73}La_{0.27}FeAs₂ are suppressed and bulk SC up to 20 K emerges. Using the x=0.046 sample as a representative, we present the superconducting properties of the Co-CaLa112 FBS. In particular, microscopic coexistence of AFM and SC in this system is revealed by combined μ SR, susceptibility and neutron scattering measurements. We contrast this behavior with the related 10-3-8 compound $Ca_{10}(Pt_3As_8)((Fe_{1-x}Pt_x)_2As_2)_5$,

which has similar FeAs interlayer spacing as Co-CaLa112, but displays no AFM-SC coexistence. We interpret this difference in terms of the nature of the spacer layer, which is metallic in the 112 compound but insulating in the 10-3-8 system.

Single crystals of Ca_{0.74(1})La_{0.26(1)}(Fe_{1-x}Co_x)As₂ were grown out of self-flux at the ratio of CaAs : LaAs : FeAs : CoAs : As = 1.3 : 0.5 : 1-x : x : 0.7⁴. Sizable single crystals were obtained by rinsing off flux in distilled water. No impurity phases were observed⁹. Zero field (ZF) and longitudinal field (LF) μ SR experiments on ~ 200 mg of single crystals with random orientations were performed in a conventional Helium gas flow cryostat in TRIUMF, Canada. Single crystal neutron diffractions were collected on the x = 0.025 sample using HB-1A triple-axis spectrometer located at the High Flux Isotope Reactor of the Oak Ridge National Laboratory.

Since both La and Co concentrations can vary, wavelength dispersive spectroscopy (WDS) measurements were performed on at least 5 pieces in each batch to determine the concentration of the sample. The result is summarized in Fig. 1 (a), showing that the ratio of $x_{\rm WDS}/x_{\rm nominal}$ is ~ 0.63. Throughout the paper, we take x to be the x_{WDS} value. The maximum Co doping achieved is at x = 0.065 while the growth with higher Co concentrations is unsuccessful. The concentration of La in each batch has a random variation as 0.270(4), 0.250(10), 0.269(3), 0.259(5), 0.249(7), 0.264(2)and 0.270(6) for x = 0, 0.008, 0.025, 0.033, 0.046, 0.056and 0.065, respectively. Since La concentration shows some variation, we label it as 0.26(1) in the chemical formula for simplicity. In each batch, the FeAs interlayer distance is inferred by measuring the (0, 0, l) X-ray peaks diffracted from the *ab* planes of several single crystals. For x = 0, the interlayer distance is $d \approx 10.39$ Å, compa-



Figure 1. $Ca_{0.74(1)}La_{0.26(1)}(Fe_{1-x}Co_x)As_2$: (a) The $x_{nominal}$ vs. x_{WDS} and the evolution of the FeAs interlayer distance d with x_{WDS} . Inset: single crystals against the 1 mm scale. (b) The temperature dependent normalized resistance R/R_{300K} for representative samples. The 50% criterion to infer T_c from resistivity is depicted for x = 0.025 sample. (c) The derivative of R/R_{300K} vs. T for the x = 0 and x = 0.008 samples. The criteria to infer T_s and T_m are depicted. (d) The temperature dependent ZFC and FC data with $H \parallel ab$. For the x = 0.025 sample, the value of $4\pi\chi$ is averaged on four pieces. The criterion to infer T_c from susceptibility is depicted. (e) The temperature dependent Hall coefficient for the x = 0 and x = 0.033 samples.

rable to the value in the 10-3-8 FBS¹⁰. Upon Co doping, the interlayer distance shrinks, decreasing by 0.22% at x = 0.065. This is comparable to the decrease of the interlayer distance at similar Co doping in BaFe₂As₂¹¹.

Figure 1 (b) shows the representative temperature dependence of R/R_{300K} , highlighting the resistive anomalies in the x = 0 and x = 0.008 samples. The derivatives of the R/R_{300K} with temperature for these two samples are shown in Fig. 1(c). Two-kink features are observed in $dR/R_{300K}/dT$ with the higher temperature kink associated with the monoclinic to triclinic phase transition and the lower temperature kink related to the paramagnetic to antiferromagnetic phase transition⁴. The structural phase transition temperature T_s and the magnetic phase transition tempe



Figure 2. $\operatorname{Ca}_{0.74(1)}\operatorname{La}_{0.26(1)}(\operatorname{Fe}_{0.954}\operatorname{Co}_{0.046})\operatorname{As}_2$: (a) The H_{c2} data inferred using the 50% criterion. Inset: the anisotropy parameter of the upper critical field $\gamma_H = H_{c2}^{\perp ab}/H_{c2}^{\parallel ab}$. (b) The C_p/T vs. T. (c) The field dependent critical current density at various temperatures. (d) Normalized pinning force $f = F_p/F_{p,max}$ vs reduced field $h = H/H_{irr}$ at various temperatures. The data were fitted by $f = Ah^p(1-h)^q$ with the parameters p = 1.14 and q = 3.24.

20 K in the x = 0.046 sample and finally is suppressed back to 16 K in the x = 0.065 sample. Figure 1(d) shows the temperature dependent susceptibility data taken at 5 Oe. Except for the x = 0.025 sample, the ZFC $4\pi\chi$ data show a relatively sharp drop below T_c and saturate at low temperature with the magnitude of ZFC $4\pi\chi$ at 2 K spreading from -110% to -120%, which are comparable to the ones in the prototype Co doped $Ba122^{11}$, suggesting 100% of SC shielding fraction here. Because of demagnetization effects, when a thin disk of radius a and thickness of $c \ll a$ is placed in a field $H \parallel a$, its intrinsic susceptibility is given by $\chi_{\text{intrinsic}} = \chi_{\text{exp}}/(1 - 4\pi N \chi_{\text{exp}})$, where $N = 0.5\pi c/a$ and χ_{exp} is the value in Fig. 1(d). For the x = 0.025 batch, the average c/a ratio of the four pieces measured is 0.10 and $4\pi \chi_{exp}$ at 2 K is -90%, resulting in an average SC shielding fraction of 80% at 2 K without saturation. The small Meissner fraction inferred from the FC data indicates strong flux pinning, a common feature in FBS. The representative Hall coefficient data taken for the x = 0 and x = 0.033 samples are presented in Fig. 1(e). Their negative values indicate that electron carriers dominate the transport properties.

As a representative, the superconducting properties of the x = 0.046 sample are shown in Fig. 2. Figure 2(a) presents the upper critical field $H_{c_2}(T)$, which is determined using the 50% criterion shown in Fig. 1(b). The anisotropy parameter of the upper critical field $\gamma_H = H_{c2}^{\perp ab}/H_{c2}^{\parallel ab}$ is around 4.7. Since the effective mass anisotropy Γ is related to γ_H by $\Gamma = \gamma_H^2 = m^{*\perp ab}/m^{*\parallel ab}$, the mass anisotropy is around 22. Note that $\gamma_H \approx 4.7$ in 112 is smaller than $\gamma_H \approx 8$ in the 10-3-8 compound, which has similar FeAs interlayer distance but insulat-

ing spacer layers^{10,12}. This suggests a stronger FeAs interlayer coupling in 112 arising from the metallic spacer layers. Figure 2(b) presents the temperature dependent specific heat C_p taken at H = 0 T. A bump in C_p associated with the superconducting phase transition appears, confirming bulk superconductivity in this sample. By the equal entropy construction shown in Fig. 2(b), the heat capacity jump $\Delta C_p/T|_{T_c}$ is 6.7 mJ/mole-Fe- K^2 at $T_c \approx 16$ K. This value follows the Budko-Ni-Canfield(BNC) log-log plot quite well¹³, suggesting that $C_p \propto T_c^3$. Since most of the FBS superconductors follow this BNC scaling¹⁴, this may suggest an $S\pm$ pairing symmetry in CaLa112. The field dependent current density J_c at various temperatures is shown in Fig. 2(c). We have calculated the critical current density based on the Bean model¹⁵, $J_c = 20 \frac{\triangle M}{w(1-\frac{w}{3l})}$, where $\triangle M = M_+ - M_-$, and M_{+} (M_{-}) is the magnetization associated with increasing (decreasing) field; w, l is the width and length of the sample separately. At 2 K, J_c reaches 2.2×10^5 A/cm^2 , comparable to $FeTe_{0.5}Se_{0.5}$ and LiFeAs but lower than $Ba_0.6K_0.4Fe_2As_2$ and $SmFeAsO_{1-x}^{16}$. To understand the mechanism of the vortex motion, the normalized pinning force $f = F_p/F_{p,max}$ as a function of reduced field $(h = H/H_{irr})$ is plotted in Fig. 2(d), where $F_p = J_c \times \mu_0 H^{17}$. All curves can be scaled well and characterized by a maximum near h = 0.25. This value is smaller than most FBS, but close to $h_{max}=0.28$ for $FeTe_{0.7}Se_{0.3}^{18}$, suggesting that both surface pinning and small size normal core pinning contribute to the vortex motion.

The interplay of structure, antiferromagnetism (AFM) and SC has been one of the most studied topics in FBS, especially because spin fluctuations are believed to play an important role in the pairing mechanism¹⁹⁻²¹. To determine the phase diagram, and particularly to resolve if microscopic coexistence between SC and AFM exists in the Co doped CaLa112, ZF $\mu {\rm SR}$ measurements were performed to estimate the magnetic volume fraction of the superconducting samples. As a representative, the ZF asymmetry spectra of the x = 0.033 sample at several temperatures are shown in Fig. 3(a). Although no feature associated with a structural/magnetic phase transition is observed in the resistivity measurements, upon decreasing the temperature from 35 K, a fast relaxing front end is absent at 20 K but clearly shows up at 8 K in Fig. 3(a), suggesting the development of magnetic order in this sample at low temperature. The ZF asymmetry spectra are fitted with the function

$$A_{ZF}(t) = A[f_T \exp(-\frac{1}{2}(\sigma t)^2) + (1 - f_T) \exp(-\lambda t)].$$
(1)

Here f_T is the transverse function and denotes the fast relaxing component coming from the static magnetic order. σ is the fast transverse relaxation rate of μ^+ . $(1 - f_T)$ is the longitudinal fraction, representing the fraction of muons with spins parallel to the local magnetic field in the region with static magnetic order and/or muons in the paramagnetic volume. The longitudinal fraction



 $Ca_{0.74(1)}La_{0.26(1)}(Fe_{1-x}Co_x)As_2$: (a) The rep-Figure 3. resentative ZF μ SR data of the x = 0.033 sample. (b) The temperature dependent ordered magnetic volume fraction V_{mag} determined from the fitting of the ZF μ SR asymmetry spectra. (c) The fast transverse relaxation rate σ inferred from the ZF μ SR asymmetry spectra. (d) The integrated intensity of the $(0\ 2\ 0)$ nuclear neutron peak and the intensity of the $(0.5 \ 0.5 \ 0.5)$ magnetic neutron peak. (e) The temperature-doping level (T - x) phase diagram of $Ca_{0.74(1)}La_{0.26(1)}(Fe_{1-x}Co_x)As_2$. For $x = 0, 0.008, T_s$ and T_m are the structural and magnetic phase transition determined from the dR/dT, respectively. For x = 0.025 and 0.033, T_m is inferred by the ZF μSR data. $T_c^{50\%}$ is the SC transition temperature determined using the 50% criterion shown in Fig. 1(b). T_c^{Mag} is determined from the susceptibility data using the criterion shown in Fig. 1(d).

only undergoes the spin lattice relaxation with the rate $\lambda = 1/T_1$.

The Gaussian relaxation form arises from the magnetic field produced by randomly oriented magnetic moments, as expected in our Co-CaLa112 sample. For an ideally isotropic and fully ordered system, f_T is expected to be 0.67 while the f_T values at 2 K in x = 0, 0.025 and 0.033 samples are 0.75, 0.72 and 0.58, respectively. The slightly larger values in the x = 0 and 0.025 samples likely arise from the field anisotropy in these randomly packed platelike single crystals. By setting the magnetic volume in the x = 0 sample to be 100% as proved reasonable in Ref.⁴, we calculate the magnetic volume of the other samples, as shown in Fig. 3(b). For the x = 0.025 sample, due to the sample inhomogeneity, around 6.4% of the sample is already magnetic at 50 K, but for the rest of the sample, AFM develops below 31 K and the magnetic volume



Figure 4. The coefficient g as function of the tight-binding parameters t_0 and t_1 in Eq. (4), under the constraint $t_2 = -t_0 - t_1$ to maintain the perfect nesting condition at $k_z = 0$. Note that g = 0 at the black lines, whereas g < 0 in the blue-shaded region (implying AFM-SC microscopic phase coexistence) and g > 0 and in the red-shaded region (implying AFM-SC macroscopic phase separation).

fraction V_{mag} saturates below 20 K with $V_{\text{mag}} \approx 96\%$ at 2 K. For the x = 0.033 sample, AFM appears below 12 K and V_{mag} increases up to 76% at 2 K without saturation. The fast transverse relaxation rate σ is shown in Fig. 3(c). Since σ is proportional to the size of the magnetic moment, which is 1.0 μ_B /Fe in the x = 0 sample as revealed by neutron diffraction⁴, assuming that the μ^+ sites remain similar in these measured samples, the magnetic moment in the x = 0.033 sample is $0.6\mu_B/\text{Fe}$ while it remains $1.0\mu_B/\text{Fe}$ in the x = 0.025 sample. The neutron diffraction data taken on a x = 0.025 single crystal are presented in Fig. 3(d). The integrated $(0\ 2\ 0)$ nuclear peak intensity sharply increases below 35 K, similar to the one in the x = 0 sample⁴, marking the occurrence of a structural phase transition. The intensity of the (0.5)0.5 0.5) magnetic peak abruptly increases below 28 K, indicating the development of long range magnetic ordering, which is consistent with the μ SR data shown in Fig. 3(b).

Based on the data we discussed above, a T - x phase diagram is constructed in Fig. 3(e). Upon Co doping, the structural/magnetic phase transitions are suppressed and SC up to 20 K emerges. For the x = 0.025 sample, the magnetic volume fraction determined from the μ SR data is 96%. The SC volume fraction determined from the susceptibility data is 80%. For the x = 0.033 sample, the SC volume fraction is 100% while the magnetic volume fraction is at least 76% at 2 K, which has the trend to sharply increase further at even lower temperature. Therefore, there is clearly microscopic coexistence between SC and AFM in x = 0.025 and 0.033 samples, similar to most doped Ba122 compounds and the Ca_{1-x}La_xFeAs₂²²⁻³¹.

It is instructive to compare these results for the 112 $Ca_{1-x}La_xFeAs_2$ compound with those for the 10-3-8

 $Ca_{10}(Pt_3As_8)((Fe_{1-x}Pt_x)_2As_2)_5$ system. Both of them have similar atomic constituents and very close values for the interlayer FeAs distance. However, in contrast to the 112, where an extended AFM-SC coexistence region emerges, the 10-3-8 shows no coexistence - or at best a very limited region of $coexistence^{32,33}$. One of the most salient differences between these two classes of compounds is the fact that in the 10-3-8, the spacer layer is insulating, whereas in the 112 it is metallic. This difference is manifest, for instance, in the larger H_{c2} anisotropy of the former ($\gamma_H \approx 8$) over the latter ($\gamma_H \approx 4.7$). Presumably, the existence of a metallic spacer layer enhances the FeAs interlayer coupling in the 112, making it more three-dimensional. Although several factors could be at play, it is tempting to attribute the presence of the AFM-SC coexistence region in these systems to the difference in their degree of three-dimensionality promoted by the distinct characters of the spacer layers.

In order to investigate whether the more pronounced k_z band dispersion of the 112 material favors the microscopic coexistence of AFM and SC, we consider a toy two-band model widely employed in the FBS to study the competition of \overrightarrow{AFM} and $\overrightarrow{SC^{34-36}}$. This model is characterized by a hole-pocket with dispersion ξ_h at the center of the Brillouin zone and an electron-pocket with dispersion ξ_e at the corner of the Brillouin zone. The fate of the competing AFM-SC phases is determined by a single coefficient g, which depends on the quartic coefficient of the microscopically-derived Ginzburg-Landau expansion⁹: if g > 0, the competition between the phase is so strong that there is no coexistence, whereas if q < 0, their competition is weak enough to allow them to coexist microscopically. In the hypothetical perfect nesting limit, $\xi_e = -\xi_h$, s^{+-} SC and AFM are at the verge of coexistence or macroscopic phase separation, with q = 0. Deviations from perfect nesting then determine whether g becomes positive or negative. Previously, deviations of perfect nesting arising from the in-plane band dispersions were studied 34,36 . Here, we consider deviations arising from the out-of-plane band dispersion, and write $\xi_e = -\xi_h + \lambda b (k_z)$, with the general k_z -dispersion:

$$b(k_z) = t_0 + t_1 \cos(p_z) + t_2 \cos(2p_z) \tag{2}$$

To ensure that the system is nested at $k_z = 0$, the tight-binding coefficients are constrained to $t_2 = -t_0 - t_1$. In Fig. 4⁹, we compute the value of g in the (t_0, t_1) parameter space. Clearly, g < 0 in a wide region of the parameter space, showing that in general the k_z dispersion can promote microscopic coexistence between SC and AFM. Thus, this simple calculation lends support to the idea that the enhanced interlayer coupling in the 112 promoted by the metallic spacer contributes to the stabilization of a regime of microscopic AFM-SC coexistence in the phase diagram.

In summary, we have mapped out the T - x phase diagram of the Ca_{0.74(1)}La_{0.26(1)}(Fe_{1-x}Co_x)As₂ superconductors. Microscopic coexistence between AFM and SC exists in this FBS. A phenomenological two-band model

suggests the dispersion along k_z direction may favors AFM-SC microscopic coexistence over phase separation.

Acknowledgments.Work at UCLA was supported by the NSF DMREF DMR-1435672. Work at ORNL's High Flux Isotope Reactor was sponsored by the Scientific User Facilities Division, BES, DOE. Work at Columbia

* Corresponding author: nini@physics.ucla.edu

- ¹ K. Y, Watanabe. T, Hirano. M and Hosono. H, J. Am. Chem. Soc., 130, 3296 (2008) (document)
- ² Katayama, N. et al., J. Phys. Soc. Jpn., 82, 123702 (2013) (document)
- ³ H. Yakita, et al., J. Am. Chem. Soc., 136 846 (2014) (document)
- ⁴ S. jiang, et al., Phys. Rev. B 93, 054522 (2016) (document)
- ⁵ Li, M. Y. et al., Phys. Rev. B, 91, 045112 (2015) (document)
- ⁶ H. Yakita, H. Ogino, A. Sala, T. Okada, A. Yamamoto, K. Kishio, A. Iyo, H. Eisaki and J. Shimoyama, Supercond. Sci. Technol. 28, 065001 (2015). (document)
- ⁷ H. Yakita, H. Ogino, A. Sala, T. Okada, A. Yamamoto, K. Kishio, A. Iyo, H. Eisaki and J. Shimoyama, Physica C, 518, 14 (2015)
- ⁸ X. Xing, W. Zhou, B. Xu, N. Li, Y. Sun, Y. Zhang and Z. Shi, J. Phys. Soc, Jpn 84, 075001 (2015). (document)
- ⁹ supplimentary materials. (document)
- ¹⁰ Ni Ni, et al., Proc. Natl. Acad. Sci, 108, E1019(2011) (document)
- ¹¹ N. Ni, et al., Phys, Rev. B 78, 214515 (2008) (document)
- ¹² Z. J. Xiang, et al., Phys. Rev. 85, 224527 (2012) (document)
- ¹³ J. S. Kim, B. D. Faeth, and G. R. Stewart, Phys. Rev. B 86, 054509 (2012). (document)
- ¹⁴ S. L. Bud'ko, et al., Phys. Rev. B 89, 014510 (2014) (document)
- ¹⁵ C. P. Bean, Rev. Mod. Phys., 36, 31 (1964) (document)
- ¹⁶ T. Taen, Y. Tsuchiya, Y. Nakajima, and T. Tamegai, Phys. Rev. B, 80, 092502 (2009) (document)
- 17 D. Dew-Hughes, Philos. Mag., 30, 293 (1974) (document)
- ¹⁸ M. Bonura, E. Giannini, R. Viennois, and C. Senatore, Phys. Rev. B, 85, 134532 (2012) (document)
- ¹⁹ J. Zhao, et al., Nat. mat 7, 953 (2008) (document)
- ²⁰ S. Nandi, et al., Phys. Rew. Lett., 104, 057006 (2010)
- ²¹ X. Lu, et al., Phys. Rev. Lett. 110, 257001 (2013) (document)
- ²² D. K. Pratt, W. Tian, A. Kreyssig, J. L. Zarestky, S. Nandi, N. Ni, S. L. Bud'ko, P. C. Canfield, A. I. Goldman, and R. J. McQueeney, Phys. Rev. Lett. **103**, 087001 (2009). (document)

- ²³ S. Avci, O. Chmaissem, E. A. Goremychkin, S. Rosenkranz, J.-P. Castellan, D. Y. Chung, I. S. Todorov, J. A. Schlueter, H. Claus, M. G. Kanatzidis, A. Daoud-Aladine, D. Khalyavin, and R. Osborn Phys. Rev. B. 83, 172503 (2011).
- ²⁴ M.-H. Julien, H. Mayaffre, M. Horvatic, C. Berthier, X. D. Zhang, W. Wu, G. F. Chen, N. L. Wang and J. L. Luo, Eur. Phys. Lett. 87 37001 (2009).
- ²⁵ E. Wiesenmayer, H. Luetkens, G. Pascua, R. Khasanov, A. Amato, H. Potts, B. Banusch, H.-H. Klauss, and D. Johrendt, Phys. Rev. Lett. **107**, 237001 (2011).
- ²⁶ P. Marsik, K. W. Kim, A. Dubroka, M. Rössle, V. K. Malik, L. Schulz, C. N. Wang, Ch. Niedermayer, A. J. Drew, M. Willis, T. Wolf, and C. Bernhard, Phys. Rev. Lett. **105**, 057001 (2010).
- ²⁷ L. Ma, G. F. Ji, J. Dai, X. R. Lu, M. J. Eom, J. S. Kim, B. Normand, and W. Yu, Phys. Rev. Lett. **109**, 197002 (2012)
- ²⁸ M. Yi, Y. Zhang, Z.-K. Liu, X. Ding, J.-H. Chu, A. F. Kemper, N. Plonka, B. Moritz, M. Hashimoto, S.-K. Mo, Z. Hussain, T. P. Devereaux, I. R. Fisher, H. H. Wen, Z.-X. Shen, and D. H. Lu, Nature Comm. **5**, 3711 (2014).
- ²⁹ S. Kawasaki, T. Mabuchi, S. Maeda, T. Adachi, T. Mizukami, K. Kudo, M. Nohara, and G. Zheng. Phys. Rev. B 92, 180508 (2015).
- ³⁰ Y. Jia, et al. Appl. Phys. Lett., 93, 032503 (2008)
- ³¹ X. L. Dong, Phys. Rev. B 92, 064515 (2015) (document)
- ³² N. Ni, et al., Phys. Rev. B 87, 060507(R) (2013) (document)
- ³³ K. Cho, et al., Phys. Rev. B 85, 020504(R) (2012).
 (document)
- ³⁴ A. B. Vorontsov, M. G. Vavilov, and A. V. Chubukov, Phys. Rev. B **79**, 060508 (2009); *ibid* Phys. Rev. B **81**, 174538 (2010). (document)
- ³⁵ D. Parker, M. G. Vavilov, A. V. Chubukov, and I. I. Mazin, Phys. Rev. B 80, 100508 (2009).
- ³⁶ R. M. Fernandes, D. K. Pratt, W. Tian, J. Zarestky, A. Kreyssig, S. Nandi, M. G. Kim, A. Thaler, N. Ni, P. C. Canfield, R. J. McQueeney, J. Schmalian, and A. I. Goldman, Phys. Rev. B **81**, 140501 (2010); R. M. Fernandes and J. Schmalian, Phys. Rev. B **82**, 014520 (2010). (document)