



# CHORUS

This is the accepted manuscript made available via CHORUS. The article has been published as:

## Role of Ce 4f hybridization in the origin of magnetism in nanoceria

V. K. Paidi, D. L. Brewster, J. W. Freeland, C. A. Roberts, and J. van Lierop

Phys. Rev. B **99**, 180403 — Published 6 May 2019

DOI: [10.1103/PhysRevB.99.180403](https://doi.org/10.1103/PhysRevB.99.180403)

# Role of Ce 4*f* hybridization in the origin of magnetism in nanoceria

V. K. Paidi,<sup>1</sup> D. L. Brewes,<sup>2</sup> J. W. Freeland,<sup>2</sup> C. A. Roberts,<sup>3</sup> and J. van Lierop<sup>1</sup>

<sup>1</sup>*Department of Physics and Astronomy, University of Manitoba, Winnipeg, Manitoba, R3T 2N2, Canada*

<sup>2</sup>*Advanced Photon Source, Argonne National Laboratory, Argonne, Illinois 60439, USA*

<sup>3</sup>*Toyota Motor Engineering and Manufacturing North America Inc.,  
1555 Woodridge Avenue, Ann Arbor, Michigan 48105, USA*

Nanoscale CeO<sub>2</sub> (nanoceria) is a prototypical system that presents d<sup>0</sup> ferromagnetism. Using a combination of x-ray absorption spectroscopy, x-ray magnetic circular dichroism and modelling, we show that nano-structure, defects and disorder, and non-stoichiometry create magnetically polarized Ce 4*f* and O 2*p* hybridized states captured by the vacancy orbitals ( $V_{orb}$ ) that are vital to ferromagnetism. Further, we demonstrate that foreign ions (Fe and Co) enhance the moment at Ce 4*f* sites while the number of  $V_{orb}$  is unchanged, pointing clearly to the mechanism of orbital hybridization being key missing ingredient to understanding the unexpected ferromagnetism in many nanoscale dilute magnetic oxides and semiconductors.

Defects, disorder, and non-stoichiometry are considered to be the key ingredients for d<sup>0</sup> magnetism in nanoscale wide band-gap oxides. d<sup>0</sup> magnetism has drawn significant interest as reflected by the many reproducible experimental observations of unexpected ferromagnetism in bulk-nonmagnetic oxides such as CeO<sub>2</sub>, ZnO, HfO<sub>2</sub>, Al<sub>2</sub>O<sub>3</sub>, In<sub>2</sub>O<sub>3</sub>, SnO<sub>2</sub> and many dilute magnetic oxides[1–8]. In general these materials have been quite puzzling due to the challenge of identifying the exact origin of the magnetism and distinguishing its spin and orbital character. It has been shown that nanoscale CeO<sub>2</sub> (nanoceria) is the prototypical system that has extensive spontaneous ferromagnetism with no magnetic cations[9]. The physics of this magnetism has been enigmatic. At first, the magnetism was attributed to most obvious candidate, exchange interactions between localized electron spin moments resulting from the oxygen vacancies [1]; first-principles calculations revealed that the vacancies (especially those at the surface) can induce magnetic moments in nanoceria[10, 11]. Later, the ferromagnetism was attributed to only sub-20 nm nanoceria with no obvious dependence on oxygen vacancies[12]. Others reported that mixed valence Ce<sup>3+</sup>/Ce<sup>4+</sup> pairs on the surface were responsible[13]. Recently, a model based on a giant orbital paramagnetism phenomenon[14] that occurs in a mesoscopic quasi-two-dimensional configuration with dilute magnetically active sites has been proposed. Despite d<sup>0</sup> behavior in nanoceria being widely reproducible[1, 9, 10, 12, 14–18], an understanding of the physics behind the nanomagnetism with the three key ingredients is still lacking.

In this work, we focus on the fundamental problem related to identifying the origin of the magnetism in nanoceria and ascertaining the mechanisms that affect the magnetic properties. We use local probes of the electronic structure and magnetism (e.g. x-ray absorption spectroscopy and x-ray magnetic circular dichroism, Mössbauer spectroscopy) combined with conventional magnetometry to provide insights into the underlying physics. Although there are earlier reports on the

element specific magnetism of nanoceria[17–19], because of the weak XMCD signal explicit evidence of the spin and orbital contributions to the magnetic moments of the Ce 4*f* states are still lacking. **Using electronic structure, surface and bulk magnetism measurements and simulations we unambiguously demonstrate that vacancy orbitals ( $V_{orb}$ ), Ce 4*f* – O 2*p* hybridization, and their affect on the Ce<sup>3+</sup> spin and orbital angular momenta are fundamental to understanding the origins of the long range ferromagnetic order.** Additionally, we have identified that foreign ions (Fe and Co) on nanoceria enhances the ferromagnetic moment at the Ce 4*f* sites, and a microscopic mechanism is proposed to explain the origin of magnetism in nanoscale oxide semiconductors.

Nanoceria[20], and Fe and Co decorated nanoceria were prepared as described in Ref. [21, 22]. The surface densities (chosen for no secondary phase formation) were 1.11 Fe/nm<sup>2</sup> and 3.57 Co/nm<sup>2</sup>[21, 22]. X-ray diffraction (XRD) pattern refinements yielded identical CeO<sub>2</sub> cubic Fm $\bar{3}$ m structures for all systems[23]. Transmission electron micrographs (TEM) and high-angle annular dark-field images were consistent with the XRD analysis. Crystallite sizes were of the order of 20 nm in diameter and lattice constants were  $5.411 \pm 0.001$  Å. XRD, TEM and Mössbauer spectroscopy (see Ref. [23]) results confirmed that no secondary phases (e.g. metal oxides) were present, as do the hard and soft x-ray absorption measurements discussed below. To identify the overall magnetism  $M(\mu_0 H)$  measurements were performed[23].  $M(\mu_0 H)$  of nanoceria shows a coercivity of  $\sim 50$  mT and saturation magnetization ( $M_s$ ) of  $\sim 4$  Am<sup>-1</sup>. Co and Fe decorated nanoceria  $M_s$ 's were  $\sim 4$  Am<sup>-1</sup> and  $7$  Am<sup>-1</sup>, respectively, in agreement with many reports in the literatures (see Ref. [9] and references therein).

Because the electronic and magnetic properties of Ce ions depend strongly on the localized and delocalized 4*f* electron states, x-ray absorption near edge structure (XANES) experiments were performed to identify and quantify the oxidation state of Ce ions in nanoceria, Fe-decorated nanoceria (Fe-CeO<sub>2</sub>) and Co-decorated




FIG. 1. (a) The normalized XANES spectra were fitted with Gaussian functions. To exclude the effects of the edge jump from fits an arctan function was included, as shown. (b) Fourier transforms represent raw data without correcting for phase shifts. Theoretical fits are the solid lines. (c) Ce  $M_{4,5}$  edge XAS data and the simulation. Charge transfer effects with  $4f^0 + 4f^1 \underline{L}$  ground and  $4f^1 + 4f^2 \underline{L}$  final states are included in order to match the experimental spectra as discussed in the text. (d) Representation of charge transfer effect between O  $2p$  ligand and Ce  $4f$  are shown;  $\underline{c}$  is core hole on Ce.

nanoceria (Co-CeO<sub>2</sub>). As shown in figure 1a, XANES spectra exhibit a doublet due to the interaction between the  $4f$  orbitals of the Ce atoms and  $2p$  orbitals of oxygen ligands. The peculiar doublet consists of four observed peaks[24–26]. Component A is assigned to the transition from the Ce  $2p$  shell to  $5d$  shell (final state  $2p4f^05d^1$  with no  $f$  electrons) while component B is assigned to the excitation from the  $2p$  shell to  $5d$  shell along with an electron being excited from the O  $2p$  shell to the Ce  $4f$  shell, thus leaving a hole in the valence band (final state  $2p4f^15d^1v$ ;  $v$  is the hole). Component C is assigned to Ce<sup>3+</sup>, and component D is assigned to the  $2p_{3/2} \rightarrow 4f$  quadrupole transition that is a consequence of  $5d$  admixtures to the  $4f$  states[27]. The concentrations of Ce<sup>3+</sup> from spectral weighting were estimated to be  $20 \pm 2\%$ . In nanoceria each Ce atom ( $[\text{Xe}]4f^15d^16s^2$ ) can donate four electrons to bonding orbitals with two O ( $1s^22s^22p^4$ ) atoms. When an oxygen vacancy is formed, the two electrons previously occupying  $p$  orbitals of the O atom are free to distribute. The localized electrons around Ce atoms changes the oxidation state from Ce<sup>4+</sup> to Ce<sup>3+</sup>. The constant Ce<sup>3+</sup>( $4f^1$ ) is as expected since the Fe and Co ions are surface decorating the nanoceria (i.e. Fe and Co ions distributed randomly on the surface of the nanoceria crystallites, bonding covalently through

available O ions, as shown experimentally in Refereces [21, 22]).

In order to gain insights into the local environment around Ce ions, we examined the extended x-ray absorption fine structure (EXAFS). Fourier transformed data and the corresponding EXAFS oscillations are shown in figure 1b. Spectral fits identify that the bond distances of first shell Ce – O systems are of  $2.31 \pm 0.04 \text{ \AA}$ . The coordination number (see Ref. [23] for details) and structural disorder around Ce (identified by Debye-Waller factors) increases in Fe-CeO<sub>2</sub> and Co-CeO<sub>2</sub>. The Ce  $L_3$  edge XAS results show that for all systems, the Ce sites exist between Ce<sup>3+</sup> ( $4f^1 \underline{v}$ ) and Ce<sup>4+</sup> ( $4f^0$ ) character, with a hole ( $\underline{v}$ ) in the O  $2p$  valence band.

To describe the  $f$  electrons, their occupancy, and electronic structure at the Ce sites, we used the Ce  $M_{4,5}$  edge XAS (probes directly the valence  $4f$  states by exciting electrons from  $3d$  core orbitals, and gives insights to the ground state) in combination with atomic multiplet calculations based on a simplified Anderson impurity model[28, 29]. The  $M_{4,5}$  edge XAS spectra (Fig. 1c) of nanoceria consists of main peaks at 884.6 and 902.4 eV and additional weaker satellite peaks at 889.8 and 908.0 eV. The energy splitting between Ce  $M_{4,5}$  edges is due to the spin-orbit coupling with the  $3d_{5/2}$  and  $3d_{3/2}$  core-holes. The primary features of the Ce  $M_{4,5}$  edge XAS spectra originate from electric-dipole allowed transitions from  $3d^{10}4f^n \rightarrow 3d^94f^{n+1}$ [29]. For nanoceria, experimental spectra are simulated including Coulomb, exchange, and spin-orbit interactions by considering only  $3d^{10}4f^0 \rightarrow 3d^94f^1$  and  $3d^{10}4f^1 \rightarrow 3d^94f^2$  configurations. Results indicated that if we assumed only oxygen vacancies and the ground states were due to  $4f^0$  and  $4f^1$  atomic-like multiplets, the experimental spectra could not be modelled successfully (see Fig. S2 of Ref. [23]). In order to understand the Ce  $M_{4,5}$  edge XAS spectra, especially the origin of the higher energy satellites, we focused on the ligand hole contribution to the  $3d^{10}4f^0$  ground state (from charge fluctuations in initial and final states due to hole on oxygen ligand). A schematic representation of a cluster consisting of a Ce ion surrounded by eight O ions is shown in Fig. 1d. Because of the strong Ce  $4f - O 2p$  hybridization, the initial state of the transition is described by  $3d^{10}4f^0 + 3d^{10}\underline{L}4f^1$  and the final state by  $3d^94f^1 + 3d^9\underline{L}4f^2$  (where  $\underline{L}$  describes a hole in the O  $2p$  band[30]). The two configurations in the final state form bonding ( $3d^94f^1$ ) and antibonding ( $3d^9\underline{L}4f^1$ ) orbital combinations. Four additional terms  $\Delta E_{gs}$ ,  $T_{gs}$ ,  $\Delta E_{fs}$ , and  $T_{fs}$  are defined to describe the relative energies and interactions of these initial and final states[29, 31]. Here  $\Delta E_{gs} = E(3d^{10}\underline{L}4f^1) - E(3d^{10}4f^0)$  is the charge transfer energy between two ground states, and  $T_{gs} = \langle (3d^{10}\underline{L}4f^1) | H | (3d^{10}4f^0) \rangle$  is the effective hopping-integral connecting the two ground state configurations. Similarly  $\Delta E_{fs} = E(3d^9\underline{L}4f^2) - E(3d^94f^1)$  and  $T_{fs} = \langle (3d^9\underline{L}4f^2) | H | (3d^94f^1) \rangle$  are charge transfer




FIG. 2. Ce  $M_{4,5}$  TEY(surface) and TFY(bulk) XMCD spectra evidencing the magnetic moment at Ce  $4f$  sites. (a) Co-CeO<sub>2</sub> TEY XMCD and simulation are shown. (b,c) A comparison of Ce  $M_{4,5}$  XAS and XMCD is shown. The origin of the energy axis of the simulated spectra has been chosen to align with the maximum intensity peak of the  $M_5$  edge and the simulated spectra is reduced by a factor of twelve to match the experimental intensity of nanoceria.

and hopping integrals of the final state[23]. Our simulation was modelled with 77%  $3d^{10}4f^0$  and 23%  $3d^{10}\underline{L}4f^1$  ground state configuration and  $\Delta E_{gs} = 2.0$  eV and  $T_{gs} = 0.77$  eV. The  $\Delta E_{fs}$  is defined as the sum of  $\Delta E_{gs} + U_{ff} - U_{fd}$ , where  $U_{ff}$  represent the Coulomb repulsion and  $U_{fd}$  the core-valence repulsion integrals. Our simulation agrees best with the experimental data with  $\Delta E_{fs} = -2.5$  eV. For a purely Ce<sup>4+</sup> based system the Ce  $M_{4,5}$  edge  $\Delta E_{fs} = -1.5$  eV[32]. In lanthanides it is expected that  $U_{ff} > U_{fd}$  due to the smaller orbital radius[28]. However, in nanoceria,  $U_{fd} > U_{ff}$  indicates that the charge transfer energy is reduced due to covalent Ce  $4f - O 2p$  states in this mixed valency system. Earlier, on the basis of band-structure calculations it was shown that ceria is less ionic[33].

Covalent orbitals play a major role in understanding the origin of magnetism. In trivalent Ce compounds such as CeRh<sub>3</sub>B<sub>2</sub> and CeCuSi the magnetism is due to highly localized  $4f$  electrons. By contrast in tetra-

valent  $\alpha$ -ceria compounds CeFe<sub>2</sub> or CeCo<sub>5</sub>, the magnetism is from hybridization between  $4f$  and conduction electrons[34]. The results of density functional theory calculations (LDA+U, LSDA+U, LDA/GGA + U) of nanoceria are controversial. Some studies support charge localization in the oxygen vacancies[10, 11] as the source of the magnetism. Other studies identify Ce vacancies[35, 36] as responsible for ferromagnetism (via superexchange between localized electrons in vacancies and neighboring Ce sites). Finally, some challenge both arguments[37], leaving the question unresolved. Identifying the origin of magnetism in nanoceria (via bulk magnetization techniques such as magnetometry and susceptometry) is complex due to the challenges in decoupling the contributions from Ce mixed valence states and oxygen vacancies. X-ray magnetic circular dichroism (XMCD) is a sensitive tool to investigate the source of magnetism at an elemental atomic level via the excitation of core level electrons to unoccupied states above the Fermi level ( $E_F$ ). XMCD experiments have the advantage of being site and orbital selective due to the electric (or quadrupole) selection rules. To gain insights into the role of the  $4f$  electrons' contribution (conduction or hybridized) we performed surface and bulk sensitive XMCD measurements simultaneously using total electron yield (TEY) and total fluorescence yield (TFY) over the  $M_{4,5}$  edges; TEY probes the first  $\sim 2$  nm of the surface while TFY measures the complete sample but is prone to self-absorption effects[38]. In Fig. 2a we present the 10 K artifact free[39]  $\pm 5$  T XMCD spectra, the TEY Co-CeO<sub>2</sub> Ce  $M_{5,4}$  XMCD, is most representative due to the least amount of surface charging. Note that ceria is a poor conductor, and Co-CeO<sub>2</sub>'s conductivity is high compared to that of Fe-CeO<sub>2</sub> and CeO<sub>2</sub> which made it difficult to measure a clean XMCD spectra in TEY for the Fe and CeO<sub>2</sub> samples. Both TEY and TFY XMCD spectra clearly identify that the Ce  $4f$  electrons unambiguously carry a magnetic moment on both the surface and in the bulk.

To quantify the magnetic moment, XMCD spectra were simulated using Xclaim[40] for the  $3d^{10}4f^1 \rightarrow 3d^94f^2$  transition in the atomic limit. The contributions of the XMCD spectral orbital and spin magnetic moments obtained from the surface and bulk contributions

	Co-CeO <sub>2</sub> TEY/surface	CeO <sub>2</sub> TFY	Fe-CeO <sub>2</sub> TFY	Co-CeO <sub>2</sub> TFY
$\langle L_z \rangle$ ( $\hbar$ )	-0.24(1)	-0.24(1)	-0.36(2)	-0.48(2)
$\langle S_z \rangle$ ( $\hbar$ )	0.03(1)	0.03(1)	0.05(1)	0.06(2)
$\langle J_z \rangle$ ( $\hbar$ )	-0.21(1)	-0.21(1)	-0.32(2)	-0.42(2)
$\langle L_z \rangle / \langle S_z \rangle$	-8	-8	-7.2	-8

TABLE I. Contributions of the z-component of the orbital and spin magnetic moments obtained from the TEY (surface) XMCD simulations of Co-CeO<sub>2</sub> and TFY (bulk) XMCD of CeO<sub>2</sub>, Fe-CeO<sub>2</sub> and Co-CeO<sub>2</sub> nanocrystallites.

are in table I. This dichroic signal is explicit evidence of Ce sites carrying magnetizable moments. In general, the spectral shape of the Ce  $M_{4,5}$  edges are indicative of a ground state total angular momentum ( $J = \frac{5}{2}$  for a pure state  $4f^1$  state). Any changes in the XMCD spectral shape can be attributed to different values of  $J$  contributing to the ground state[34, 41]. It is important to note that the simulated spectra are for a pure  $J = \frac{5}{2}$  state are not in complete agreement with experiment (e.g. Fig. 2a – negative peak present at the  $M_5$  edge and an overestimation(underestimation) of  $M_5(M_4)$  dichroic signals). Interestingly, nanoceria’s Ce  $M_{4,5}$  XMCD spectral line shape is different from  $\text{CeRh}_3\text{B}_2$  and  $\text{CeCuSi}$ [34] (where the ground state is pure  $J = \frac{5}{2}$  and magnetism is due to  $4f$  conduction electrons) but quite similar to the XMCD spectra of  $\text{CeFe}_2$  and a Ce/Fe multilayer (ground state is a mixture of  $J = \frac{5}{2}$  and  $J = \frac{7}{2}$ [34, 42]). This is indicative of Ce  $4f$  electrons being strongly hybridized with the O  $2p$  valence band. At the  $M$  edges, although the TFY XAS signal is distorted[43] because of self absorption (Fig. 2b) the TFY XMCD (Fig. 2c) signal is similar to TEY XMCD (surface). The TFY XMCD magnitude increases in the order of  $\text{CeO}_2 < \text{Fe-CeO}_2 < \text{Co-CeO}_2$ . Results identify that foreign ions with intrinsic moments (such as Fe and Co) enhances[23] the overall magnetic moment at Ce  $4f$  increases (Table. I).

XMCD measurements (atomic magnetism) identify the average magnetic moment as  $0.18 \mu_B/\text{Ce}$ [23], and if all Ce  $4f$  magnetic states are contributing to the ferromagnetism, the  $\sim 20$  nm  $\text{CeO}_2$  crystallites are expected to show  $\sim 2000 \mu_B/\text{crystallite}$ . In contrast SQUID magnetometry measures the magnetization from the Ce  $4f$ ,  $V_{orb}$ , and hybridization contributions with  $M_s=2 \mu_B/\text{crystallite}$  identifying that the ferromagnetic volume fraction is only 0.1% (see Ref. [23] for XMCD and SQUID magnetometry moment calculations). **Clearly, not all Ce  $4f$  states are involved in the magnetism; only the fraction associated with the  $V_{orb}$  and/or hybridization (it follows that because of the low fraction, only Ce  $4f - \text{O } 2p$  hybridized states that are captured in the delocalized  $V_{orb}$  are associated) are responsible.**

The radial extent of Ce  $4f$  orbitals[44] are very small (0.54 Å) and that limits the Ce  $4f - \text{O } 2p$  covalent mixing to be relatively low as supported by various DFT/LDA/GGA calculations[45]. However, the size (0.5 to 0.8 nm diameter) of the  $V_{orb}$  are large (see Ref. [23] for calculation) and less localized compared to the Ce  $4f$  states. This is consistent with first principle calculations that found the size of  $V_{orb}$  at  $\sim 1.0$  nm[46]. Note that only the trapped Ce  $4f$  states in the  $V_{orb}$  can polarize spin moments (due to their delocalized nature) on the hybridized states and be responsible for the long range ferromagnetic order. The residual  $4f$  states that are not in the vicinity of  $V_{orb}$  cannot contribute to the ferromagnetism due to the lack of the hybridized magnetic states. If the number of  $V_{orb}$  are constant, introducing




FIG. 3. Graphical illustration of the magnetic model. Ce  $4f$  magnetic states,  $V_{orb}$ , and hybridized Ce  $4f$  and O  $2p$  states are shown. Ce  $4f$  states captured in the  $V_{orb}$  polarizes the hybridized states and provides a channel to mediate the ferromagnetism. Shaded region illustrates the magnetic exchange process as discussed in the text.

foreign transition metal ions (Fe or Co) impacts Ce  $4f - \text{O } 2p$  hybridization and further promotes a robust, yet weak, ferromagnetism. Figure 3 shows the illustration of this microscopic model. This description is consistent with the observation that air or  $\text{O}_2$  annealed  $d^0$  nanoscale magnetic oxides exhibit reduced or annihilated magnetism[1, 9, 47], as  $\text{O}_2$  fills the vacancies resulting in a deficiency of  $V_{orb}$  coupling channels.

In summary, we have found a possible pathway to explain the origin of ferromagnetism in the dilute magnetic oxide nanoceria. Using a combination of electronic structure, elemental and bulk sensitive magnetism techniques we show that  $V_{orb}$ , Ce  $4f$  spin and orbital angular momentum, and hybridization with O  $2p$  states are crucial for the magnetic ordering. The concept of magnetism from hybridized Ce  $4f - \text{O } 2p$  states in trapped  $V_{orb}$  is a missing link to understand the ferromagnetism in nanoceria. In closing, this work provides unambiguous experimental evidence of the origin of ferromagnetism in nanoceria, and demonstrates that this hybridization concept may be a solid foundation from which to explain the unexpected ferromagnetism in  $\text{ZnO}$ ,  $\text{HfO}_2$ ,  $\text{Al}_2\text{O}_3$ ,  $\text{In}_2\text{O}_3$ ,  $\text{SnO}_2$  and many other dilute magnetic oxides and semiconductors (where O  $2p$  hole states are key players, and their hybridization with host or guest metal ions changes the density of states) that present similar magnetism.

We thank Dr. D. J. Keavney for assistance with the XAS and XMCD measurements, and Dr. S. M. Heald for helping with the XAFS measurements on Co-CeO<sub>2</sub>. VKP and JvL acknowledge funding from the Natural Sciences and Engineering Research Council of Canada (RGPIN-2018-05012) and the Canada Foundation for Innovation. Use of the Advanced Photon Source at Argonne National Laboratories was supported by the US DOE under con-

tract DE-AC02-06CH11357.

- 
- [1] A. Sundaresan, R. Bhargavi, N. Rangarajan, U. Siddesh, and C. Rao, *Physical Review B* **74**, 161306 (2006).
- [2] B. B. Straumal, A. A. Mazilkin, S. G. Protasova, A. A. Myatiev, P. B. Straumal, G. Schütz, P. A. Van Aken, E. Goering, and B. Baretzky, *Physical Review B* **79**, 205206 (2009).
- [3] J. Chaboy, R. Boada, C. Piquer, M. Laguna-Marco, M. García-Hernández, N. Carmona, J. Llopis, M. Ruíz-González, J. González-Calbet, J. Fernández, *et al.*, *Physical Review B* **82**, 064411 (2010).
- [4] A. S. Esmaily, M. Venkatesan, S. Sen, and J. Coey, *Physical Review Materials* **2**, 054405 (2018).
- [5] J. Coey, *Solid State Sciences* **7**, 660 (2005).
- [6] J. Coey and S. Chambers, *MRS bulletin* **33**, 1053 (2008).
- [7] T. Dietl, *Nature materials* **9**, 965 (2010).
- [8] R. Green, T. Regier, B. Leedahl, J. McLeod, X. Xu, G. Chang, E. Kurmaev, and A. Moewes, *Physical review letters* **115**, 167401 (2015).
- [9] K. Ackland and J. Coey, *Physics Reports* (2018).
- [10] M. Ge, H. Wang, E. Liu, J. Liu, J. Jiang, Y. Li, Z. Xu, and H. Li, *Applied Physics Letters* **93**, 062505 (2008).
- [11] X. Han, J. Lee, and H.-I. Yoo, *Physical Review B* **79**, 100403 (2009).
- [12] Y. Liu, Z. Lockman, A. Aziz, and J. MacManus-Driscoll, *Journal of Physics: Condensed Matter* **20**, 165201 (2008).
- [13] M. Li, S. Ge, W. Qiao, L. Zhang, Y. Zuo, and S. Yan, *Applied Physics Letters* **94**, 152511 (2009).
- [14] M. Coey, K. Ackland, M. Venkatesan, and S. Sen, *Nature Physics* **12**, 694 (2016).
- [15] N. Paunović, Z. Dohčević-Mitrović, R. Scurtu, S. Aškračić, M. Prekajski, B. Matović, and Z. V. Popović, *Nanoscale* **4**, 5469 (2012).
- [16] K. Ackland, L. M. Monzon, M. Venkatesan, and J. Coey, *IEEE transactions on magnetics* **47**, 3509 (2011).
- [17] S.-Y. Chen, C.-H. Tsai, M.-Z. Huang, D.-C. Yan, T.-W. Huang, A. Gloter, C.-L. Chen, H.-J. Lin, C.-T. Chen, and C.-L. Dong, *The Journal of Physical Chemistry C* **116**, 8707 (2012).
- [18] W. Lee, S.-Y. Chen, Y.-S. Chen, C.-L. Dong, H.-J. Lin, C.-T. Chen, and A. Gloter, *The Journal of Physical Chemistry C* **118**, 26359 (2014).
- [19] D.-Z. Peng, S.-Y. Chen, C.-L. Chen, A. Gloter, F.-T. Huang, C.-L. Dong, T.-S. Chan, J.-M. Chen, J.-F. Lee, H.-J. Lin, *et al.*, *Langmuir* **30**, 10430 (2014).
- [20] C.I. Kasei Co., Ltd. NanoTek powder.
- [21] C. A. Roberts, D. Prieto-Centurion, Y. Nagai, Y. F. Nishimura, R. D. Desautels, J. Van Lierop, P. T. Fanson, and J. M. Notestein, *The Journal of Physical Chemistry C* **119**, 4224 (2015).
- [22] T. C. Peck, G. K. Reddy, M. Jones, and C. A. Roberts, *The Journal of Physical Chemistry C* **121**, 8435 (2017).
- [23] See Supplemental Material at [URL will be inserted by publisher] for details of XRD, TEM, HAADF, BET, ICP, XAS simulations, XAFS analysis, SQUID magnetometry and  $V_{orb}$  calculations.
- [24] H. Dexpert, R. Karnatak, J.-M. Esteva, J. Connerade, M. Gasgnier, P. Caro, and L. Albert, *Physical Review B* **36**, 1750 (1987).
- [25] G. Kaindl, G. Schmiester, E. Sampathkumaran, and P. Wachter, *Physical Review B* **38**, 10174 (1988).
- [26] A. Soldatov, T. Ivanchenko, S. Della Longa, A. Kotani, Y. Iwamoto, and A. Bianconi, *Physical Review B* **50**, 5074 (1994).
- [27] T. Sham, R. Gordon, and S. Heald, *Physical Review B* **72**, 035113 (2005).
- [28] F. De Groot, *Coordination Chemistry Reviews* **249**, 31 (2005).
- [29] B. Thole, G. Van der Laan, J. Fuggle, G. Sawatzky, R. Karnatak, and J.-M. Esteva, *Physical Review B* **32**, 5107 (1985).
- [30] S. Butorin, D. Mancini, J.-H. Guo, N. Wassdahl, J. Nordgren, M. Nakazawa, S. Tanaka, T. Uozumi, A. Kotani, Y. Ma, *et al.*, *Physical review letters* **77**, 574 (1996).
- [31] R. D. Cowan, *The theory of atomic structure and spectra*, 3 (Univ of California Press, 1981).
- [32] M. W. Loble, J. M. Keith, A. B. Altman, S. C. E. Stieber, E. R. Batista, K. S. Boland, S. D. Conradson, D. L. Clark, J. Lezama Pacheco, S. A. Kozimor, *et al.*, *Journal of the American Chemical Society* **137**, 2506 (2015).
- [33] D. Koelling, A. Boring, and J. Wood, *Solid state communications* **47**, 227 (1983).
- [34] J. P. Schillé, F. Bertran, M. Finazzi, C. Brouder, J. Kappler, and G. Krill, *Physical Review B* **50**, 2985 (1994).
- [35] V. Fernandes, R. Mossaneck, P. Schio, J. Klein, A. De Oliveira, W. Ortiz, N. Mattoso, J. Valalda, W. Schreiner, M. Abbate, *et al.*, *Physical Review B* **80**, 035202 (2009).
- [36] L. Zhan-Sheng, M. Dong-Wei, Z. Jing, X. Guo-Liang, and Y. Zong-Xian, *Chinese Physics B* **21**, 047505 (2012).
- [37] P. Keating, D. Scanlon, and G. Watson, *Journal of Physics: Condensed Matter* **21**, 405502 (2009).
- [38] W. Fuhrman, J. Leiner, J. Freeland, M. van Veenendaal, S. Koohpayeh, W. A. Phelan, T. McQueen, and C. Broholm, *Physical Review B* **99**, 020401 (2019).
- [39] The XMCD spectra were obtained as the difference of the corrected x-ray-absorption spectra for both left and right circularly polarizations. To make sure that the final XMCD spectra were free of experimental artifacts, such as those from charging effects, spectra were also collected for the opposite applied field direction.
- [40] J. Fernández-Rodríguez, B. Toby, and M. van Veenendaal, *Journal of Electron Spectroscopy and Related Phenomena* **202**, 81 (2015).
- [41] G. Van der Laan, B. Thole, G. Sawatzky, J. Fuggle, and R. Karnatak, *Journal of Physics C: Solid State Physics* **19**, 817 (1986).
- [42] M. Finazzi, F. De Groot, A.-M. Dias, B. Kierren, F. Bertran, P. Sainctavit, J.-P. Kappler, O. Schulte, W. Felsch, and G. Krill, *Physical review letters* **75**, 4654 (1995).
- [43] S. Butorin, D. Mancini, J.-H. Guo, N. Wassdahl, and J. Nordgren, *Journal of Alloys and Compounds* **225**, 230 (1995).
- [44] Z. Barandiarán and L. Seijo, *The Journal of chemical physics* **119**, 3785 (2003).
- [45] J. Paier, C. Penschke, and J. Sauer, *Chemical reviews* **113**, 3949 (2013).
- [46] T. Heng, D.-C. Qi, T. Berlijn, J. Yi, K. Yang, Y. Dai, Y. Feng, I. Santoso, C. Sánchez-Hanke, X. Gao, *et al.*, *Physical review letters* **105**, 207201 (2010).
- [47] N. H. Hong, N. Poirot, and J. Sakai, *Applied physics letters* **89**, 042503 (2006).