

This is the accepted manuscript made available via CHORUS. The article has been published as:

Magnetic Field Induced Orbital Polarization in Cubic YbInNi_4 : Determining the Quartet Ground State Using X-Ray Linear Dichroism

T. Willers, J. C. Cezar, N. B. Brookes, Z. Hu, F. Strigari, P. Körner, N. Hollmann, D. Schmitz, A. Bianchi, Z. Fisk, A. Tanaka, L. H. Tjeng, and A. Severing

Phys. Rev. Lett. **107**, 236402 — Published 29 November 2011

DOI: [10.1103/PhysRevLett.107.236402](https://doi.org/10.1103/PhysRevLett.107.236402)

Magnetic field induced orbital polarization in cubic YbInNi₄: determining the quartet ground state using x-ray linear dichroism.

T. Willers,¹ J.C. Cezar,² N.B. Brookes,² Z. Hu,³ F. Strigari,¹ P. Körner,¹ N. Hollmann,³
D. Schmitz,⁴ A. Bianchi,⁵ Z. Fisk,⁶ A. Tanaka,⁷ L. H. Tjeng,³ and A. Severing¹

¹*Institute of Physics II, University of Cologne, Zùlpicher StraÙe 77, D-50937 Cologne, Germany*

²*European Synchrotron Radiation Facility (ESRF), B.P. 220, F-38043 Grenoble Cédex, France*

³*Max Planck Institute for Chemical Physics of Solids,
Nöthnizer StraÙe 40, D-01187 Dresden, Germany*

⁴*Helmholtz-Center Berlin for Materials and Energy,
Albert-Einstein-StraÙe 15, D-12489 Berlin, Germany*

⁵*Département de Physique, Université de Montréal, Montréal, Quebec H3C 3J7, Canada*

⁶*University of California, Irvine, California 92697, USA*

⁷*Department of Quantum Matter, ADSM Hiroshima University, Higashi-Hiroshima 739-8530, Japan*
(Dated: September 29, 2011)

We have been able to induce a linear dichroic signal in the Yb M_5 x-ray absorption white line of cubic YbInNi₄ by the application of a magnetic field. The non-zero integrated intensity of the magnetic field induced dichroic spectrum indicates a net non-cubic $4f$ orbital polarization. A quantitative analysis of the temperature and field strength dependence establishes that the crystal field ground state is a Γ_8 quartet. The results demonstrate the potential of magnetic field induced linear dichroism as a new powerful approach for the investigation of the degeneracy and orbital degrees of freedom of cubic heavy fermion and Kondo systems.

PACS numbers: 71.27.+a, 75.10.Dg, 75.30.Mb, 78.70.Dm

We have recently shown that polarization dependent soft x-ray absorption spectroscopy (XAS) at the rare earth $M_{4,5}$ edges is a very powerful method to determine the crystal-field (CF) ground state wave function of tetragonal $4f$ Kondo and heavy-fermion systems [1–3]. It provides valuable information complementary to neutron scattering experiments.

In this study we would like to explore the possibilities to also apply XAS for *cubic* $4f$ systems, a class of materials with quite intriguing properties [4–22]. At first sight, one does not expect any polarization dependence since a cubic wave function is isotropic for a dipole allowed transition process and consequently, one would not expect to gain insight about the question which of the cubic wave functions forms actually the ground state. However, here we demonstrate that the application of a magnetic field can provide key information about the nature of the ground state wave function. We have done so using YbInNi₄ as an exemplary model system: it has the relative simplicity of a stable valent system and yet there is a long standing debate about its ground state wave function [23–25]. Very recently, also a new interesting scenario has been proposed for the closely related compound Yb_{0.5}Y_{0.5}InCu₄ [26]. We will show that the ground state of YbInNi₄ is a quartet. Our results demonstrate that - in addition to neutron [7, 12] and (resonant) x-ray scattering [9–11, 13] - we have a new approach for the determination of the degeneracy and orbital degrees of freedom in cubic rare-earth systems, which is important for the modeling of the properties of many of the Kondo insulators [4] as well as of the fascinating phenomena occurring in,

for instance, the large group of skutterudite compounds, which includes metal-to-insulator transitions, superconductivity and multipolar order/discorder [14–22].

The static susceptibility of YbInNi₄ shows a Curie-Weiss behavior with nearly the full Yb³⁺ moment down to about 3 K where it orders magnetically [24]. In the cubic C15b structure of YbInNi₄ the 8 fold degenerate Hund's rule ground state of Yb³⁺ with $J=7/2$ splits in cubic site symmetry into two doublets $|\Gamma_6\rangle$ and $|\Gamma_7\rangle$, and one quartet $|\Gamma_8\rangle$ which can be written in a $|J_z\rangle$ basis as

$$\begin{aligned} |\Gamma_6\rangle &= \begin{cases} c'|-7/2\rangle + d'|+1/2\rangle \\ c|+7/2\rangle + d|-1/2\rangle \end{cases} \\ |\Gamma_7\rangle &= \begin{cases} a'|-5/2\rangle - b'|+3/2\rangle \\ a|+5/2\rangle - b|-3/2\rangle \end{cases} \\ |\Gamma_8\rangle &= \begin{cases} |\widetilde{\Gamma_6}\rangle = \begin{cases} d'|-7/2\rangle - c'|+1/2\rangle \\ d|+7/2\rangle - c|-1/2\rangle \end{cases} \\ |\widetilde{\Gamma_7}\rangle = \begin{cases} b'|-5/2\rangle + a'|+3/2\rangle \\ b|+5/2\rangle + a|-3/2\rangle \end{cases} \end{cases} \end{aligned} \quad (1)$$

with $a^2 + b^2 = a'^2 + b'^2 = c^2 + d^2 = c'^2 + d'^2 = 1$. Here a more general expression is chosen which holds in the presence of an applied magnetic field, i.e. it shows how states are modified by an applied magnetic field. For cubic site symmetry and no applied field $a=a'$, $b=b'$, $c=c'$, and $d=d'$ is valid and $a = \sqrt{3/4}$ and $c = \sqrt{5/12}$, so that the CF problem reduces to determining which one of the three states forms the ground state [28].

YbInNi₄ is a good example for how different techniques can yield different CF results. Figure 1 summarizes some crystal-field scenarios which have been suggested for this system: inelastic neutron scattering studies infer a $|\Gamma_8\rangle$




FIG. 1: (color online) Crystal-field schemes as published in [23–26].

quartet ground state [23], while specific heat, magnetization and ESR experiments claimed to have found a $|\Gamma_7\rangle$ doublet ground state [24, 25]. Yet, one can envision even another scenario: measurements on YbInCu_4 with 50% Y doping proposed a CF scheme with a quasi-quartet ground state as shown on the right in Fig. 1 [26]. Here we note that the crystal field scheme in YbInNi_4 and the high temperature phase of the YbInCu_4 system is commonly regarded as being very similar [27].

Figure 2 displays the $4f$ angular hole distributions of the $|\Gamma_6\rangle$, $|\Gamma_7\rangle$, and $|\Gamma_8\rangle$ CF states (upper panel, from left to right) of the $\text{Yb } 4f_{7/2}^{13}$ multiplet in cubic symmetry. We also calculate the corresponding $3d \rightarrow 4f$ XAS, which all consist of one single line: the final state has a full $4f^{14}$ shell, and the intensity is all concentrated in the $3d_{5/2}$ resonance (M_5 absorption edge) since transitions to the $3d_{3/2}$ state (M_4 absorption edge) are dipole forbidden in the limit that the CF splitting is negligible compared to the $4f$ spin-orbit interaction. None of these CF states show a polarization dependence for linearly polarized x-rays coming in with the electric field vector \mathbf{E} parallel (red) or perpendicular (blue dashed) to the $[001]$ crystallographic axis.

The situation changes considerably when a magnetic field is applied, e.g. along the $[001]$ or z -axis. Apart from inducing a Zeeman splitting, the $|\Gamma_8\rangle$ state becomes split into the $|\widetilde{\Gamma}_6\rangle$ and $|\widetilde{\Gamma}_7\rangle$ states. While the $4f$ spatial distribution of the $|\Gamma_7\rangle$, and $|\Gamma_6\rangle$ does not change, that of the $|\Gamma_8\rangle$ is transformed into quite different looking spatial distributions of the $|\widetilde{\Gamma}_6\rangle$ and $|\widetilde{\Gamma}_7\rangle$ states, respectively. This is shown in the lower panel of Fig. 2. It is important to note that the spatial distributions of the $|\widetilde{\Gamma}_6\rangle$ and $|\widetilde{\Gamma}_7\rangle$ are *not cubic*. Consequently, there will be a linear polarization dependence in the XAS for these two states as also illustrated in Fig. 2: the so-called magnetic-field-induced linear dichroic (MILD) signal, i.e. the magnetic-field-induced difference of the absorption between linearly po-




FIG. 2: (color online) Angular hole distributions and their corresponding polarization dependent M_5 XAS spectra of the $4f_{7/2}^{13}$ wave functions in cubic symmetry. The upper panel shows the distributions and spectra in the absence of an external field. The lower panel displays the decomposition of the $|\Gamma_8\rangle$ distribution in the presence of magnetic field into the $|\widetilde{\Gamma}_6\rangle$ and $|\widetilde{\Gamma}_7\rangle$ (see eq. 1), together with their corresponding spectra. The orientation of the applied magnetic field and electric field vector \mathbf{E} of the linearly polarized light relative to the $[001]$ crystallographic axis is also depicted.

larized x-rays coming in with the electric field vector \mathbf{E} parallel (red) or perpendicular (blue dashed) to the $[001]$ crystallographic axis, is significant. The MILD signals of these two states are equally large but has opposite signs as the sum must vanish.

A polarization dependent XAS experiment in a magnetic field can therefore give a simple yes/no answer to the question whether the ground state in a cubic material is a quartet or a doublet [29]. Yet, the above mentioned analysis is valid for CF splittings very much larger than the Zeeman splitting. For the YbInNi_4 system, the CF splittings could be of the same order of magnitude as the Zeeman splitting: the CF energies are about 4 meV and the Zeeman splitting amounts to 0.5–1.0 meV when a 5 T field is applied. The cubic wave functions are then no longer eigenstates of the system, and all states, doublets and quartets, will give rise to a polarization dependence in the XAS. A quantitative analysis needs to include all these effects as is done in the following sections.

The XAS measurements were performed at the ID08 beamline of the ESRF. The photon energy resolution at the Yb M_5 edge ($h\nu \approx 1520$ eV) was set at ≈ 1.4 eV. The magnetic field is applied perpendicular to the Poynting vector of the light. The electric field vector \mathbf{E} of the linearly polarized light can be switched between par-




FIG. 3: (color online) Experimental x-ray absorption spectrum of YbInNi₄ at the Yb M₅ edge for linearly polarized light coming in with the electric field vector \mathbf{E} parallel (red) and perpendicular (blue) to the magnetic field oriented close to the [001] crystallographic axis.

allel and perpendicular to the magnetic field, and the degree of linear polarization was $\approx 99\%$. The spectra were recorded using the total electron yield method in an ultra-high-vacuum chamber with a base pressure of 5×10^{-10} mbar. Clean sample areas were obtained by cleaving two YbInNi₄ crystals *in-situ*. The (100) cleavage surface was set 5° off the magnetic field direction in order to avoid the Lorentz force hindering the electrons to escape the sample surface. The temperature was measured using a certified Lake Shore Cernox thermoelement on the sample holder 5 mm above the sample and the temperature gradient on the sample holder had been calibrated before the experiment.

Figure 3 shows the x-ray absorption spectra of YbInNi₄ at the Yb M₅ edge for the electric field vector \mathbf{E} parallel and perpendicular to the magnetic field which is oriented close to the [001] crystallographic axis. The measurements were carried out with the sample at 6.5 ± 0.5 K for fields up to 5 T. The magnetic field clearly induces a significant polarization dependence. For a quantitative analysis, we now define the magnetic-field-induced linear dichroism as $\text{MILD} = (I_\perp - I_\parallel) / (2I_\perp + I_\parallel)$ where I_\parallel and I_\perp are the integrated absorption intensities for light polarized parallel and perpendicular to the magnetic field.

To interpret the data, we start with the remark that the linear dichroism for the pure $|J_z\rangle$ states are -0.357 for $|1/2\rangle$, -0.214 for $|3/2\rangle$, +0.071 for $|5/2\rangle$, and +0.500 for $|7/2\rangle$. At 0 K and in the limit that the Zeeman splitting is much smaller than the CF splittings, the MILD for the cubic states ($a = \sqrt{3/4}$ and $c = \sqrt{5/12}$ in eq. 1) are zero for the $|\Gamma_6\rangle$ and $|\Gamma_7\rangle$, and +0.143 for the $|\widetilde{\Gamma}_6\rangle$ of the Zeeman split $|\Gamma_8\rangle$ manifold. Note that the $|\widetilde{\Gamma}_6\rangle$ forms the lowest state. Taking into account the thermal occupation of the states at 6.5 K and 5 T, the MILD




FIG. 4: (color online) Magnetic field induced linear dichroism (MILD) as a function of magnetic field calculated using the CF scheme of Severing *et al.* [23] (blue), Sarrao *et al.* [24] (orange), Pagliuso *et al.* [25] (green), and Aviani *et al.* [26] (red), at 0 K (top panel) and for the temperature range between 6 and 7 K (6.5 ± 0.5 K) (bottom panel). The squares and circles in the bottom panel correspond to the measurements of two different YbInNi₄ crystals.

for the $|\Gamma_8\rangle$ manifold reduces to +0.038 because now the $|\widetilde{\Gamma}_7\rangle$ contributes to the dichroism with the opposite sign.

For YbInNi₄ we have to consider the CF energies as proposed in the scenarios displayed in Fig. 1. We have calculated the corresponding MILD as a function of magnetic field. The results for 0 K are shown in the top panel of Fig. 4. For infinitesimally small (non-zero) magnetic fields, only the Severing scenario produces an MILD with the +0.143 value mentioned above. Its MILD value increases steadily with rising magnetic fields because the lowest Zeeman state $|\widetilde{\Gamma}_6\rangle$ of the $|\Gamma_8\rangle$ manifold gains more $|J_z\rangle=|7/2\rangle$ character due to the energy lowering of the latter by the magnetic field, i.e. in eq. 1 the d coefficient increases and the d' decreases for positive external fields. This is very effective to create an increase in the MILD since this $|7/2\rangle$ carries the largest LD of all pure $|J_z\rangle$ states. The amount of increase of the MILD (and the $|7/2\rangle$ character) with field depends inversely on the magnitude of the CF splitting between the $|\widetilde{\Gamma}_6\rangle$ and $|\Gamma_6\rangle$.

The Aviani scheme also produces MILD but with smaller values: the MILD vanishes for small fields, and it increases almost linearly with increasing field for a similar reason as in the Severing scenario: the $|J_z\rangle=|7/2\rangle$ component increases in the lowest state, which is here the $|\Gamma_6\rangle$. This is described by an increase of the c coefficient and a decrease of the c' in eq. 1 for a positive field. The

slope of MILD versus field is almost identical as for the Severing scenario since the energy splitting is almost the same. The Sarrao and Pagliuso scenarios produce hardly any MILD even at large magnetic fields due to the fact that the $|3/2\rangle$ and $|5/2\rangle$ components in the $|\Gamma_7\rangle$ lowest state carry by themselves already smaller LD signals, so that the redistribution of their relative weights due to the magnetic field has little effect on the net LD.

The top panel of Fig. 4 reveals clearly that at 0 K the experiment should be performed at low fields in order to obtain optimum contrast between the Severing scenario on one hand and the other scenarios on the other hand, and at the highest possible field to distinguish the Aviani scheme from the Sarrao and Pagliuso one. In practice, 6.5 K was the lowest possible temperature which we could reach. This then changes the situation and the bottom panel of Fig. 4 displays the expected MILD for the four different scenarios for a temperature in the range between 6 and 7 K. The thermal population of the next higher Zeeman states reduces the MILD considerably, especially for the Severing scenario. Yet, the distinction between the scenarios is still large for high magnetic fields.

We now plot in the lower panel of Fig. 4 the experimental MILD at 6.5 ± 0.5 K as a function of field: it is zero for 0 T and increases to about 10.5% for 5 T. The open and full circles correspond to the two crystals, both measured twice at 5 T, once straight after cleaving and once after all the runs with different fields strengths were completed. The MILD has been determined from at least ten scans measured in sequences of parallel-perpendicular-perpendicular-parallel polarization and then been averaged. One can observe that the Severing scenario fits well to the experimental data. The Aviani scheme on the other hand, provides MILD values which are about 30% lower, a significant discrepancy. The Sarrao and Pagliuso scenarios can clearly be ruled out since the expectation values are much smaller than the measured ones.

We therefore conclude from our MILD measurements that the $|\Gamma_8\rangle$ is the only possible ground state wave function. This is consistent with the findings of recent magnetic form factor experiments [30]: the measured spatial distribution of the $4f$ magnetic moment also rules out $|\Gamma_7\rangle$ as ground state, but cannot distinguish between the $|\Gamma_6\rangle$ and $|\Gamma_8\rangle$ scenarios.

To summarize, we have demonstrated in simulations and experiment that a magnetic field induced linear dichroism (MILD) in an x-ray absorption experiment at the $3d \rightarrow 4f$ edge can give information about the ground state wave function of a rare-earth cubic compound. We have further shown that in the event of comparable Zeeman and CF energies the MILD can still give a unique result when the sample temperature is sufficiently low and well defined. The measured MILD in YbInNi_4 can only be explained with a $|\Gamma_8\rangle$ quartet ground state.

We thank M. W. Haverkort providing the CrystalFieldTheory package for Mathematica used to calculate

the wave function density plots. Z.F. acknowledges support through U.S. National Science Foundation under Grant No. NSF-DMR-0801253. T.W. and N.H. are partially supported by the Bonn-Cologne Graduate School of Physics and Astronomy.

-
- [1] P. Hansmann, A. Severing, Z. Hu, M. W. Haverkort, C. F. Chang, S. Klein, A. Tanaka, H. H. Hsieh, H.-J. Lin, C. T. Chen, et al., Phys. Rev. Lett. **100**, 066405 (2008).
- [2] T. Willers, B. Fåk, N. Hollmann, P. O. Körner, Z. Hu, A. Tanaka, D. Schmitz, M. Enderle, G. Lapertot, L. H. Tjeng, et al., Phys. Rev. B **80**, 115106 (2009).
- [3] T. Willers, Z. Hu, N. Hollmann, P. O. Körner, J. Gegner, T. Burnus, H. Fujiwara, A. Tanaka, D. Schmitz, H. H. Hsieh, et al., Phys. Rev. B **81**, 195114 (2010).
- [4] P. Riseborough, Adv. Phys. **49**, 174428 (2000).
- [5] E. Zirngiebl, B. Hillebrands, S. Blumenröder, G. Güntherodt, M. Loewenhaupt, J. M. Carpenter, K. Winzer, and Z. Fisk, Phys. Rev. B **30**, 4052 (1984).
- [6] Y. Kuramoto and N. Fukushima, J. Phys. Soc. Jpn. **67**, 583 (1998).
- [7] M. Sera, H. Ichikawa, T. Yokoo, J. Akimitsu, M. Nishi, K. Kakurai, and S. Kunii, Phys. Rev. Lett. **86**, 1578 (2001).
- [8] P. Thalmeier, R. Shiina, H. Shiba, A. Takahashi, and O. Sakai, J. Phys. Soc. Jpn. **72**, 3219 (2003).
- [9] Y. Y. Tanaka, U. Staub, S. Katsumata, K. and Lovesey, J. Lorenzo, Y. Narumi, V. Scagnoli, S. Shimomura, Y. Tabata, Y. Onuki, Y. Kuramoto, et al., Europhys. Lett. **68**, 671 (2004).
- [10] H. Kono, K. Kubo, and Y. Kuramoto, J. Phys. Soc. Jpn. **73**, 2948 (2004).
- [11] D. Mannix, Y. Tanaka, D. Carbone, N. Bernhoeft, and S. Kunii, Phys. Rev. Lett. **95**, 117206 (2005).
- [12] K. Kuwahara, K. Iwasa, M. Kohgi, N. Aso, M. Sera, and F. Iga, J. Phys. Soc. Jpn. **76**, 093702 (2007).
- [13] T. Matsumura, T. Yonemura, K. Kunimori, M. Sera, and F. Iga, Phys. Rev. Lett. **103**, 017203 (2009).
- [14] C. Sekine, T. Uchiumi, I. Shirotani, and T. Yagi, Phys. Rev. Lett. **79**, 3218 (1997).
- [15] H. Sato, Y. Abe, H. Okada, T. D. Matsuda, K. Abe, H. Sugawara, and Y. Aoki, Phys. Rev. B **62**, 15125 (2000).
- [16] E. Bauer, A. Slebarski, E. Freeman, C. Sirvent, and M. Maple, J. Phys.: Condens. Matter **13**, 4495 (2001).
- [17] E. A. Goremychkin, R. Osborn, E. D. Bauer, M. B. Maple, N. A. Frederick, W. M. Yuhasz, F. M. Woodward, and J. W. Lynn, Phys. Rev. Lett. **93**, 157003 (2004).
- [18] K. Kuwahara, K. Iwasa, M. Kohgi, K. Kaneko, N. Metoki, S. Raymond, M.-A. Méasson, J. Flouquet, H. Sugawara, Y. Aoki, et al., Phys. Rev. Lett. **95**, 107003 (2005).
- [19] T. Takimoto, Journal of the Physical Society of Japan **75**, 034714 (2006).
- [20] H. Kotegawa, H. Hidaka, T. C. Kobayashi, D. Kikuchi, H. Sugawara, and H. Sato, Phys. Rev. Lett. **99**, 156408 (2007).
- [21] R. W. Hill, S. Li, M. B. Maple, and L. Taillefer, Phys. Rev. Lett. **101**, 237005 (2008).
- [22] P.-C. Ho, T. Yanagisawa, W. M. Yuhasz, A. A. Dooraghi, C. C. Robinson, N. P. Butch, R. E. Baumbach, and M. B. Maple, Phys. Rev. B **83**, 024511 (2011).
- [23] A. Severing, E. Gratz, B. Rainford, and K. Yoshimura, Physica B **163**, 409 (1990).
- [24] J. L. Sarrao, R. Modler, R. Movshovich, A. H. Lacerda, D. Hristova, A. L. Cornelius, M. F. Hundley, J. D. Thompson, C. L. Benton, C. D. Immer, et al., Phys. Rev. B **57**, 7785 (1998).
- [25] P. G. Pagliuso, J. D. Thompson, J. L. Sarrao, M. S. Sercheli, C. Rettori, G. B. Martins, Z. Fisk, and S. B. Oseroff, Phys. Rev. B **63**, 144430 (2001).
- [26] I. Aviani, M. Očko, D. Starešinić, K. Biljakovi, A. Loidl, J. Hemberger, and J. L. Sarrao, Phys. Rev. B **79**, 165112 (2009).
- [27] T. Park, V. A. Sidorov, J. L. Sarrao, and J. D. Thompson, Phys. Rev. Lett. **96**, 046405 (2006).
- [28] Note, that the cubic symmetry fixes the sign of the wave functions. Here we define the phase relation between the $|j_z\rangle$ wave functions via $J_-|J, j_z\rangle = \hbar\sqrt{(J+j_z)(J-j_z+1)}|J, j_z-1\rangle$ for $j_z = -J, \dots, J$.
- [29] For all Kramer's ions Zeeman split quartets give rise to linear dichroism but doublets do not. The situation is different for non Kramer's ions. Here all but singlet states give rise to linear dichroism when split up by a magnetic field.
- [30] A. Severing, F. Givord, J.-X. Boucherle, T. Willers, M. Rotter, Z. Fisk, A. Bianchi, M. T. Fernandez-Diaz, A. Stunault, B. D. Rainford, et al., Phys. Rev. B **83**, 155112 (2011).