

This is the accepted manuscript made available via CHORUS. The article has been published as:

Variational Principle for Mass Transport

Dallas R. Trinkle

Phys. Rev. Lett. **121**, 235901 — Published 3 December 2018

DOI: [10.1103/PhysRevLett.121.235901](https://doi.org/10.1103/PhysRevLett.121.235901)

A variational principle for mass transport

Dallas R. Trinkle*

*Department of Materials Science and Engineering,
University of Illinois, Urbana-Champaign, Illinois 61801, USA*

(Dated: September 10, 2018)

Abstract

A variation principle for mass transport in solids is derived that recasts transport coefficients as minima of local thermodynamic average quantities. The result is independent of diffusion mechanism, and applies to amorphous and crystalline systems. This unifies different computational approaches for diffusion, and provides a framework for the creation of new approximation methods with error estimation. It gives a different physical interpretation of the Green function. Finally, the variational principle quantifies the accuracy of competing approaches for a nontrivial diffusion problem.

Keywords: diffusion; Onsager coefficients; mass transport; variational principle

Mass transport in solids is the fundamental kinetic process controlling both the evolution of materials towards equilibrium and a variety of material properties[1]. Diffusion of atoms dictates everything from the stability of amorphous materials at finite temperature, the design of nanoscaled semiconductor devices, the processing of structural metals including steels and superalloys, the performance of batteries and fuel cells, to the degradation of materials due to corrosion or even irradiation. Since Einstein[2], diffusion has been understood as mesoscale motion arising from many individual atomic displacements, with significant effort over the last century to experimentally measure and model theoretically[3, 4]. In the last forty years, computation has played an increasingly important role, with different competing approximation methods developing, combined with increasingly accurate methods to compute transition state energies for atomic processes in transport[5–7]. However, while we have increasing accuracy in predicting atomic scale mechanisms, we lack a clear methodology to compare accuracy of theoretical models that derive mesoscale transport coefficients.

The modern macroscale description of mass transport comes from Onsager’s work on nonequilibrium thermodynamics[8], where atomic fluxes \mathbf{J} are linearly proportion to small driving forces. A general driving force is the gradient of chemical potential of species α . Then, the Onsager transport coefficients are second-rank tensors $\underline{L}^{(\alpha\beta)}$ that relate steady state fluxes in species α

$$\mathbf{J}^\alpha = - \sum_{\beta} \underline{L}^{(\alpha\beta)} \nabla \mu^\beta \quad (1)$$

are steady-state fluxes in response to perturbatively small driving forces in chemical species $\nabla \mu^\beta$. These transport coefficients can also be derived from a thermodynamic extremal principle[9, 10] for maximum entropy production, making the Onsager matrix symmetric and positive semidefinite.

A brief, albeit incomplete list of methods to compute transport coefficients from atomic mechanisms include stochastic methods like kinetic Monte Carlo[11–15], master-equation methods like the self-consistent mean-field method[16, 17] and kinetic mean-field approximations[18–20], path probability methods for irreversible thermodynamics[21–23], Green function methods[24–27], and Ritz variational methods[28–30]. The different approaches all have different computational and theoretical complexity, rely on different approximations which may or may not be controlled. However, the relationships between different approximations is not always clear, and it is difficult to determine which of two different calculations is more accurate, short of comparison to experimental results. In what follows, we derive a general expression for the mass transport coefficients

in a solid system, and then cast this non-local form into an equivalent minimization problem over *thermodynamic averages of local quantities*: a variational principle for mass transport, with a simple physical interpretation. We show that different computational approaches can be derived and compared with this principle, while also providing a framework for the development of new types of approximations for diffusion. We conclude with a quantitative comparison for a random alloy on a square lattice.

Consider a system with chemical species[31] $\alpha = \text{A, B, } \dots$, with discrete microstates $\{\chi\}$, and transitions between states. For each state χ and species α , N_χ^α of that species are at positions $\{\mathbf{x}_{\chi i}^\alpha : i = 1 \dots N_\chi^\alpha\}$. Note that the $\mathbf{x}_{\chi i}^\alpha$ are themselves functions of the state χ . If each state has an energy E_χ , then in the grand canonical ensemble, the equilibrium probability of occupying a given microstate for chemical potentials μ^α at temperature T is

$$P_\chi^0 := P_\chi^0(T, \mu^A, \dots) = \exp \left[\frac{1}{k_B T} \left(\Phi_0 + \sum_\alpha \mu^\alpha N_\chi^\alpha - E_\chi \right) \right] \quad (2)$$

where Φ_0 is a normalization constant—the grand potential—such that $\sum_\chi P_\chi^0 = 1$. If the chemical potentials were spatially *inhomogeneous*, then the term corresponding to the sum over chemistry would be $\sum_\alpha \sum_i \mu^\alpha(\mathbf{x}_{\chi i}^\alpha)$. We assume that our system can achieve equilibrium through a Markovian process, with transition rates $W(\chi \rightarrow \chi') \geq 0$; then, by detailed balance, $P_\chi^0 W(\chi \rightarrow \chi') = P_{\chi'}^0 W(\chi' \rightarrow \chi)$. If all nonzero rates conserve chemical species, then the rates $W(\chi \rightarrow \chi')$ are independent of the chemical potentials, and can only depend on the initial and final states and temperature. The master equation for the evolution of a time dependent probability $P_\chi(t)$ is

$$\frac{dP_\chi(t)}{dt} = \sum_{\chi'} P_{\chi'}(t) W_{\chi' \chi} \quad (3)$$

and we introduce the shorthand matrix form

$$W_{\chi' \chi} = \begin{cases} W(\chi' \rightarrow \chi) & : \chi \neq \chi' \\ -\sum_{\chi'} W(\chi \rightarrow \chi') & : \chi = \chi' \end{cases} \quad (4)$$

We identify steady state solutions of Eqn. 3—which may not be equilibrium solutions—as distributions where the right-hand side is zero for every χ ; we are interested in steady-state solutions that maintain infinitesimal gradients in chemical potentials, for which we will compute fluxes.

What follows is a generalization of results derived previously for a lattice gas model[27]; details are available in the supplemental material[32]. Consider a steady-state probability distribution $P_\chi^{\text{ss}} := P_\chi^{\text{ss}}(T, \mu^A, \dots, \nabla \mu^A, \dots)$ in the presence of infinitesimally small chemical potential gradient

vectors $\nabla\mu^\alpha$. This steady-state probability distribution can have time-independent fluxes \mathbf{J}^α corresponding to mass transport. For any (non-zero rate) transition $\chi \rightarrow \chi'$, we define the mass transport vector for each species α as $\delta\mathbf{x}_{\chi\chi'}^\alpha := \sum_i \mathbf{x}_{\chi'i}^\alpha - \mathbf{x}_{\chi i}^\alpha$. This is the net change in positions for all atoms of species α , as $N_\chi^\alpha = N_{\chi'}^\alpha$ when $W(\chi \rightarrow \chi') \neq 0$. Then, the flux is

$$\mathbf{J}^\alpha = V_0^{-1} \sum_{\chi\chi'} P_\chi^{\text{ss}} W_{\chi\chi'} \delta\mathbf{x}_{\chi\chi'}^\alpha \quad (5)$$

for total system volume V_0 . We make the ansatz that the steady-state probability distribution for infinitesimal gradients

$$P_\chi^{\text{ss}} = P_\chi^0 \left[1 + \frac{\delta\Phi_0}{k_B T} + \frac{1}{k_B T} \sum_\alpha \nabla\mu^\alpha \cdot \left(\boldsymbol{\eta}_\chi^\alpha + \sum_{i=1}^{N_\chi^\alpha} \mathbf{x}_{\chi i}^\alpha \right) \right] \quad (6)$$

up to first order in $\nabla\mu^\alpha$, where $\delta\Phi_0$ is a change in the normalization relative to the equilibrium distribution, and introducing the *relaxation vectors* $\boldsymbol{\eta}_\chi^\alpha$ that are to-be-determined for each state χ . These vectors are a generalization of the rate-dependent relaxation in solute-vacancy exchange[33]. If we substitute Eqn. 6 into Eqn. 3, set $dP_\chi^{\text{ss}}/dt = 0$, apply detailed balance, divide out by P_χ^0 , and require that it hold for arbitrary $\nabla\mu^\alpha$, we find

$$\sum_{\chi'} W(\chi \rightarrow \chi') \delta\mathbf{x}_{\chi\chi'}^\alpha = - \sum_{\chi'} W(\chi \rightarrow \chi') (\boldsymbol{\eta}_{\chi'}^\alpha - \boldsymbol{\eta}_\chi^\alpha). \quad (7)$$

We define the left-hand side as the velocity vector $\mathbf{b}_\chi^\alpha := \sum_{\chi'} W_{\chi\chi'} \delta\mathbf{x}_{\chi\chi'}^\alpha$, so that Eqn. 7 becomes

$$\mathbf{b}_\chi^\alpha = - \sum_{\chi'} W_{\chi\chi'} \boldsymbol{\eta}_{\chi'}^\alpha. \quad (8)$$

for the steady-state ansatz solution to be time invariant. Then, the transport coefficients $\underline{L}^{(\alpha\beta)}$ can be found by substituting the steady-state solution into Eqn. 5, while explicitly symmetrizing the summation (rewriting as $\frac{1}{2} \sum_{\chi\chi'} + \sum_{\chi'\chi}$), which gives

$$\underline{L}^{(\alpha\beta)} = \frac{1}{k_B T V_0} \left\langle \underbrace{\frac{1}{2} \sum_{\chi\chi'} W_{\chi\chi'} \delta\mathbf{x}_{\chi\chi'}^\alpha \otimes \delta\mathbf{x}_{\chi\chi'}^\beta}_{\text{uncorrelated}} - \underbrace{\mathbf{b}_\chi^\alpha \otimes \boldsymbol{\eta}_\chi^\beta}_{\text{correlated}} \right\rangle_\chi \quad (9)$$

where the two terms are the “uncorrelated” and “correlated” contributions to diffusivity[3, 34], and the average is the shorthand for $\sum_\chi P_\chi^0$.

While Eqn. 9 has the form of a simple thermal average, the primary complication is the solution of Eqn. 8, which requires the pseudoinversion of the singular rate matrix $W_{\chi\chi'}$ over the entire state

space; this is the Green function $G_{\chi\chi'} := W_{\chi\chi'}^+$. While the rate matrix is local—as there are only a finite number of final states χ' to transition from any state χ —the Green function is known to be non-local, and difficult to compute in general. However, the governing equation for the relaxation vectors η_χ^α can be recast instead in a variational form by taking advantage of an *invariance* in Eqn. 9.

First, the separation of Eqn. 9 into correlated and uncorrelated terms is arbitrary[34, 35]. We introduce changes to the positions of atoms in a state while leaving the rate matrix unchanged: Let \mathbf{y}_χ^α be the sum of all displacements of atoms of species α in state χ . We can, without loss of generality[36], consider only cases where $\sum_\chi \mathbf{y}_\chi^\alpha = 0$. Then, the \mathbf{y}_χ^α change the displacement, velocity, and relaxation vectors

$$\begin{aligned}\widetilde{\delta\mathbf{x}}_{\chi\chi'}^\alpha &= \delta\mathbf{x}_{\chi\chi'}^\alpha + \mathbf{y}_{\chi'}^\alpha - \mathbf{y}_\chi^\alpha, & \widetilde{\mathbf{b}}_\chi^\alpha &= \mathbf{b}_\chi^\alpha + \sum_{\chi'} W_{\chi\chi'} \mathbf{y}_{\chi'}^\alpha, \\ \widetilde{\eta}_\chi^\alpha &= - \sum_{\chi'} G_{\chi\chi'} \widetilde{\mathbf{b}}_{\chi'}^\alpha = \eta_\chi^\alpha - \sum_{\chi'\chi''} G_{\chi\chi'} W_{\chi'\chi''} \mathbf{y}_{\chi''}^\alpha = \eta_\chi^\alpha - \mathbf{y}_\chi^\alpha\end{aligned}$$

as G is the pseudoinverse of W , and \mathbf{y}_χ^α is orthogonal to the right null space of W . Then, the Onsager coefficients are

$$\begin{aligned}k_B T V_0 \underline{L}^{\alpha\beta} &= \left\langle \frac{1}{2} \sum_{\chi\chi'} W_{\chi\chi'} (\delta\mathbf{x}_{\chi\chi'}^\alpha + \mathbf{y}_{\chi'}^\alpha - \mathbf{y}_\chi^\alpha) \otimes (\delta\mathbf{x}_{\chi\chi'}^\beta + \mathbf{y}_{\chi'}^\beta - \mathbf{y}_\chi^\beta) - (\mathbf{b}_\chi^\alpha + \sum_{\chi'} W_{\chi\chi'} \mathbf{y}_{\chi'}^\alpha) \otimes (\eta_\chi^\beta - \mathbf{y}_\chi^\beta) \right\rangle_\chi \\ &= \left\langle \frac{1}{2} \sum_{\chi\chi'} W_{\chi\chi'} \delta\mathbf{x}_{\chi\chi'}^\alpha \otimes \delta\mathbf{x}_{\chi\chi'}^\beta \right\rangle_\chi + \frac{1}{2} \sum_{\chi\chi'} P_\chi^0 W_{\chi\chi'} (\mathbf{y}_{\chi'}^\alpha - \mathbf{y}_\chi^\alpha) \otimes (\mathbf{y}_{\chi'}^\beta - \mathbf{y}_\chi^\beta) + \frac{1}{2} \sum_{\chi\chi'} P_\chi^0 W_{\chi\chi'} \delta\mathbf{x}_{\chi\chi'}^\alpha \otimes (\mathbf{y}_{\chi'}^\beta - \mathbf{y}_\chi^\beta) \\ &\quad + \frac{1}{2} \sum_{\chi\chi'} P_\chi^0 W_{\chi\chi'} (\mathbf{y}_{\chi'}^\alpha - \mathbf{y}_\chi^\alpha) \otimes \delta\mathbf{x}_{\chi\chi'}^\beta - \langle \mathbf{b}_\chi^\alpha \otimes \eta_\chi^\beta \rangle_\chi + \sum_\chi P_\chi^0 \mathbf{b}_\chi^\alpha \otimes \mathbf{y}_\chi^\beta - \sum_{\chi\chi'} P_\chi^0 W_{\chi\chi'} \mathbf{y}_{\chi'}^\alpha \otimes \eta_\chi^\beta + \sum_{\chi\chi'} P_\chi^0 W_{\chi\chi'} \mathbf{y}_{\chi'}^\alpha \otimes \mathbf{y}_\chi^\beta \\ &= k_B T V_0 \underline{L}^{(\alpha\beta)} - \sum_{\chi\chi'} P_\chi^0 W_{\chi\chi'} \mathbf{y}_\chi^\alpha \otimes \mathbf{y}_{\chi'}^\beta - \langle \mathbf{b}_\chi^\alpha \otimes \mathbf{y}_\chi^\beta \rangle_\chi - \langle \mathbf{y}_\chi^\alpha \otimes \mathbf{b}_\chi^\beta \rangle_\chi + \langle \mathbf{b}_\chi^\alpha \otimes \mathbf{y}_\chi^\beta \rangle_\chi + \langle \mathbf{y}_\chi^\alpha \otimes \mathbf{b}_\chi^\beta \rangle_\chi + \sum_{\chi\chi'} P_\chi^0 W_{\chi\chi'} \mathbf{y}_{\chi'}^\alpha \otimes \mathbf{y}_\chi^\beta = k_B T V_0 \underline{L}^{(\alpha\beta)}\end{aligned}$$

This requires detailed balance $P_\chi^0 W_{\chi\chi'} = P_{\chi'}^0 W_{\chi'\chi}$ and the sum rule $\sum_{\chi'} W_{\chi\chi'} = 0$. Hence, the transport coefficients are invariant under arbitrary displacements, while the “uncorrelated” and “correlated” terms themselves change.

We can exploit this invariance by noting that, for $\alpha = \beta$, the uncorrelated contribution is positive semidefinite and the correlated contribution is negative semidefinite, as $W_{\chi\chi'}$ and $G_{\chi\chi'}$ are negative semidefinite matrices. Thus, the maximum value of the correlated contribution is zero, which corresponds with the *minimal value* of the *uncorrelated* contribution, and so the equation for the transport coefficients can be rewritten as

$$\underline{L}^{(\alpha\alpha)} = \frac{1}{2k_B T V_0} \inf_{\mathbf{y}_\chi^\alpha} \left\langle \sum_{\chi\chi'} W_{\chi\chi'} \widetilde{\delta\mathbf{x}}_{\chi\chi'}^\alpha \otimes \widetilde{\delta\mathbf{x}}_{\chi\chi'}^\alpha \right\rangle_\chi, \quad (10)$$

which is a *variational principle for mass transport* involving only thermodynamic averages of local rate matrix. Here, the infimum of the tensor corresponds to the tensor with the smallest trace[37]. The values of \mathbf{y}_χ^α that minimize Eqn. 10 are found by making the generalized force from the gradient of $\ell^\alpha := k_B T V_0 \text{Tr } \underline{L}_{\text{uncorr}}^{(\alpha\alpha)} = \frac{1}{2} \left\langle \sum_{\chi'} W_{\chi\chi'} (\widetilde{\delta \mathbf{x}}_{\chi\chi'}^\alpha)^2 \right\rangle_\chi$,

$$\begin{aligned} \mathbf{f}_\chi^\alpha &:= -\frac{\partial \ell^\alpha}{\partial \mathbf{y}_\chi^\alpha} = -\frac{1}{2} \frac{\partial}{\partial \mathbf{y}_\chi^\alpha} \sum_{\chi' \chi''} P_{\chi'}^0 W_{\chi' \chi''} (\delta \mathbf{x}_{\chi' \chi''}^\alpha + \mathbf{y}_{\chi''}^\alpha - \mathbf{y}_{\chi'}^\alpha)^2 \\ &= -2P_\chi^0 \sum_{\chi'} W_{\chi\chi'} (\delta \mathbf{x}_{\chi\chi'}^\alpha + \mathbf{y}_{\chi'}^\alpha - \mathbf{y}_\chi^\alpha) = -2P_\chi^0 \widetilde{\mathbf{b}}_\chi^\alpha \end{aligned} \quad (11)$$

equal to zero; this is satisfied when $\mathbf{y}_\chi^\alpha = \boldsymbol{\eta}_\chi^\alpha$. Moreover, the arguments \mathbf{y}_χ^α that minimize ℓ^α can then be used to compute the off-diagonal contributions,

$$\underline{L}^{(\alpha\beta)} = \frac{1}{2k_B T V_0} \left\langle \sum_{\chi'} W_{\chi\chi'} \widetilde{\delta \mathbf{x}}_{\chi\chi'}^\alpha \otimes \widetilde{\delta \mathbf{x}}_{\chi\chi'}^\beta \right\rangle_\chi \bigg|_{\substack{\mathbf{y}_\chi^\alpha = \arg \inf \ell^\alpha \\ \mathbf{y}_\chi^\beta = \arg \inf \ell^\beta}} \quad (12)$$

Hence, while the $\alpha \neq \beta$ terms are not variational, they are determined by the solution of the diagonal variational problem. Eqn. 10 is similar to the Varadhan-Spohn variational form[38], which Arita *et al.* note is a powerful, albeit abstract result that is difficult to apply in practice, involving “cylinder” functions[39]; it is simpler than the alternate Ritz variational form, as there is no normalization of an eigenvector required[28–30].

This variational principle for mass transport has multiple consequences. First, it unifies multiple approaches for the computation of mass transport coefficients, including kinetic Monte Carlo, Green function methods, and self-consistent mean-field theory. Moreover, it provides a direct way to compare the accuracy of different methods: outside of the convergence of stochastic sampling errors, once a mass transport method is recast in a variational form, the minimal value of the diagonal transport coefficients is necessarily closer to the true value. It also gives a simple physical explanation for the correlation contributions in mass transport: the $\boldsymbol{\eta}_\chi^\alpha$ values are displacements that map a correlated random walk into an equivalent uncorrelated random walk with identical transport coefficients. Finally, it provides a framework for the construction of new algorithms for the computation of mass transport that requires the minimization of a thermal average; as it is based on minimization, different approximations for \mathbf{y}_χ^α can be simultaneously introduced, while the process of minimization finds the optimal solution.

In the case of a linear expansion for the relaxation vectors, the variational principle for mass transport provides a simple general expression for diffusivity. Let $\{\boldsymbol{\phi}_{\chi,n}^\alpha\}$ be a set of basis vectors so that we expand $\mathbf{y}_\chi^\alpha = \sum_n \boldsymbol{\phi}_{\chi,n}^\alpha \theta_n^\alpha$ with coefficients θ_n^α . The supplemental material Sec. S4 shows

the most general solution; here, we include the solution for the case where the basis functions are chemistry- and direction-independent: $\phi_{\chi,ni}^\alpha = \hat{e}_i \phi_{\chi,n}$ for a Cartesian orthonormal basis $\hat{e}_1, \hat{e}_2, \hat{e}_3$. Then, the coefficients that minimize Eqn. 10 can be found by solving $\sum_m \bar{W}_{nm} \theta_{mi}^\alpha = \bar{\mathbf{b}}_n^\alpha \cdot \hat{e}_i$ where,

$$\bar{W}_{nm} := \left\langle \sum_{\chi'} W_{\chi\chi'} \phi_{\chi,n} \phi_{\chi',m}^\alpha \right\rangle_\chi, \quad \bar{\mathbf{b}}_n^\alpha := \left\langle \phi_{\chi,n} \mathbf{b}_\chi^\alpha \right\rangle_\chi. \quad (13)$$

We can take the pseudoinverse of $\bar{G} := (\bar{W})^+$, and then the transport coefficients are (c.f. Eqn. S26)

$$\underline{L}_{\text{LBAM}}^{(\alpha\beta)} = \frac{1}{2k_B T V_0} \left\langle \sum_{\chi'} W_{\chi\chi'} \delta \mathbf{x}_{\chi\chi'}^\alpha \otimes \delta \mathbf{x}_{\chi\chi'}^\beta \right\rangle_\chi + \frac{1}{k_B T V_0} \sum_{nm} \left\langle \phi_{\chi,n} \mathbf{b}_\chi^\alpha \right\rangle_\chi \otimes \bar{G}_{nm} \left\langle \phi_{\chi,m} \mathbf{b}_\chi^\beta \right\rangle_\chi \quad (14)$$

where the diagonal transport coefficients $\underline{L}_{\text{LBAM}}^{(\alpha\alpha)}$ are guaranteed to be an upper bound on the true coefficients, achieving equality when the basis $\{\phi_{\chi,n}\}$ spans $\boldsymbol{\eta}_\chi^\alpha$.

We can now express existing computational approaches as attempts to solve the variational problem. For kinetic Monte Carlo[11–15], each trajectory represents a single sample in the average, while the increasing length of a trajectory attempts to converge the relaxation vectors corresponding to that single starting state. In Sec. S3, the equivalence of kinetic Monte Carlo to the variation method is shown; moreover, the use of a finite length trajectory is variational: assuming perfect sampling of initial states, and with perfect sampling of trajectories of a finite length, the transport coefficients will be greater than the true transport coefficients. If one uses accelerated KMC methods[40–44], superbins—a finite collection of states with fast internal transitions but slow escapes—are effectively collapsed onto a single *position*, which is an approximation to the relaxation vector $\boldsymbol{\eta}_\chi^\alpha$. For vacancy-mediated diffusion, the dilute Green function[26, 27] and matrix methodology[24, 25] work in a restricted state space $\{\chi\}$ where only one solute and vacancy are present, and then effectively construct a full basis in that state space. Finally, self-consistent mean-field[16, 17] and kinetic mean-field[18–20] work with a cluster expansion of chemistry- and direction-independent basis functions $\{\phi_{\chi,n}\}$ that are products of site occupancies for different chemistries. It should be noted that these latter two methods derive their solution for the parameters θ_n using a ladder of n -body correlation functions on which they invoke “closure approximations” for higher order correlation functions; in a variational framework, such closure approximations become unnecessary. Finally, when methods are framed in variational terms, we can quantitatively compare accuracy by identifying which method gives the smallest diagonal elements $\underline{L}^{(\alpha\alpha)}$, and also estimate remaining error through the average residual bias, $\langle (\widetilde{\mathbf{b}}_\chi^\alpha)^2 / (-W_{\chi\chi}) \rangle_\chi$ in Eqn. S29, or its ratio with $\langle (\mathbf{b}_\chi^\alpha)^2 / (-W_{\chi\chi}) \rangle_\chi$.

In addition to providing a common frame for existing computational methods for mass transport, we now have a new framework to develop and test new approximations, including those that are more appropriate for amorphous systems that lack crystalline order but still possess well-defined microstates. A simple example is the basis function choice $\phi_\chi^\alpha = \mathbf{b}_\chi^\alpha$; in Sec. S5 of the supplemental material, a closed-form approximation for transport coefficients is provided in Eqn. S32. This approximation involves inverting a matrix that has the same dimensionality as the number of independent chemical species; however, it only captures local correlations. We can also take the dilute Green function methodology for vacancy-mediated transport into finite solute concentrations by using the basis functions $\phi_{\chi\beta\mathbf{x}}$ that are equal to the occupancy (0 or 1) by chemistry β of a site at a vector \mathbf{x} relative to a vacancy in state χ . This approximation exactly reproduces the dilute solute limit by being equivalent to an infinite range two-body-only version of the Green function.

For a quantitative comparison of these new approximations, we consider a random binary alloy on a square lattice with a single vacancy. In this model, there is no binding energy between any species, and the jump rate for the vacancy only depends on the chemistry of the species it is exchanging: either ν_A (“solvent” exchange) or ν_B (“solute” exchange). We take $\nu_A = 1$, and consider three cases: $\nu_B = 1$ (tracer), $\nu_B = 4$ (“fast” diffuser), and $\nu_B = 0$ (frozen solute). This system has nontrivial behavior, including a percolation limit[45, 46] for $\nu_B = 0$ where the diffusivity of solvent is 0 for $c_B < 1$. To compute the transport coefficients, we use: (1) kinetic Monte Carlo on a 64×64 periodic grid, generating 256 samples of trajectories run for 4096 vacancy jumps each; the transport coefficients are computed 32 separate times to get a mean and stochastic error estimate. (2) A two-body Green function approximation (c.f. Sec. S6), which has the analytic solution (c.f. Eqn. S40),

$$\begin{aligned} \underline{L}_{\text{GF}}^{(\text{AA})} &= \mathbf{1} c_v a_0^2 \left[c_A \nu_A - \frac{c_A c_B \nu_A^2}{\nu_A + \nu_B + \frac{2f-1}{1-f}(c_A \nu_A + c_B \nu_B)} \right] \\ \underline{L}_{\text{GF}}^{(\text{BB})} &= \mathbf{1} c_v a_0^2 \left[c_B \nu_B - \frac{c_A c_B \nu_B^2}{\nu_A + \nu_B + \frac{2f-1}{1-f}(c_A \nu_A + c_B \nu_B)} \right] \end{aligned} \quad (15)$$

where $f = (\pi-1)^{-1} \approx 0.467$ is the dilute tracer correlation coefficient for a square lattice. (3) A bias basis approximation, which has the same transport coefficients as Eqn. 15 with the approximation $f = 1 - 2/(z+1) = 0.6$. (4) A self-consistent mean-field approach taking into account clusters of all orders within two jumps: $\pm\hat{x}$, $\pm\hat{y}$, $\pm\hat{x} \pm \hat{y}$, $\pm 2\hat{x}$, and $\pm 2\hat{y}$. Finally, for $\nu_B = 0$ we use a full Green function solution for vacancy diffusivity with 256 configurations of a 256×256 periodic cell, and compute a residual bias correction (RBC) for the two-body Green function results.

Fig. 1 shows the different accuracy for this binary system, where the lowest diffusivity is the most accurate. The Green function approach captures the dilute A and B limits for the tracer and fast diffuser examples, and is the most accurate of the three approaches. The largest difference is seen for the percolation case $\nu_B = 0$, where both the Green function and self-consistent mean-field methods are good approximations for $c_B \lesssim 0.2$, but begin to break down as we approach the percolation limit. In this case, solutes are creating islands where a vacancy is trapped and unable to diffuse over long distances; inside such an island, the relaxation vectors should map all “trapped” states onto the same position, producing no contribution to the diffusivity. We also see the direct simulations produce lower, more accurate, diffusivity. The size of these islands gets smaller as c_B increases, and only the self-consistent mean-field method—and only at large concentrations of solute—is able to reproduce the behavior seen by kinetic Monte Carlo. This suggests the need to go beyond the two-body basis for the Green function approach, or combining local multisite basis functions with long-range basis functions, or perhaps new approximation methods all together. One example such approach is the RBC, where following a linear basis approximation method, the residual bias vectors serve as basis vectors for a correction to the diffusivity; in the case of $\nu_B = 0$, we derive an analytic expression (c.f. Sec. S7, Eqn. S47) that has similar error to the SCMF result.

With a variational formulation of transport coefficients, we can develop new approximate methods for modeling diffusion in solids, including amorphous materials. If linear approximations are used, then basis functions provide a projection of the state space into a subspace while the variational principle provides a lower bound on transport coefficients. The selection of basis functions can be guided by physical insight—such as diffusing quasiparticles—and systematic improvement is always possible. It is also possible to construct *nonlinear* approximations to the relaxation vectors \mathbf{y}_χ^α which might require fewer parameters to describe; still, a variational principle permits relative comparisons of different methods, and a lower bound on the result. While the fundamental insight for the variational formulation came from the invariance in Eqn. 9, it can be derived as an thermodynamic extremum principle where the positions of atoms are “free” variables, connecting to Onsager’s original work.

The author thanks Pascal Bellon and Maylise Nastar for helpful conversations and suggestions for the manuscript. This research was supported in part by the U.S. Department of Energy, Office of Basic Energy Sciences, Division of Materials Sciences and Engineering under Award #DE-FG02-05ER46217, through the Frederick Seitz Materials Research Laboratory, in part by




FIG. 1. Diffusivity of “solute” atom B and “solvent” A in a random alloy on a square lattice, scaled by vacancy concentration. The vacancy exchange rate with atom A is 1, while we consider different relative rates for vacancy-B exchange and different solute concentrations from 0 to 1. The largest deviation is for the case where $\nu_B = 0$, which requires longer range correlation to capture the percolation limit near $c_B \approx 0.5$; the “percolation” simulations are averages of 256 Green function calculations on a 256×256 periodic cell.

the Office of Naval Research grant N000141210752, and in part by the National Science Foundation Award 1411106. Part of this research was performed while the author was visiting the Institute for Pure and Applied Mathematics (IPAM) at UCLA, which is supported by the National Science Foundation (NSF). The python notebook for the random alloy results in Fig. 1 is available online at Ref. 47, which makes use of the algebraic multigrid solver PyAMG[48].

* dtrinkle@illinois.edu

- [1] R. W. Balluffi, S. M. Allen, and W. C. Carter, *Kinetics of Materials* (John Wiley & Sons, Inc., 2005).
- [2] A. Einstein, Ann. d. Physik **322**, 549 (1905).
- [3] A. R. Allnatt and A. B. Lidiard, “Atomic transport in solids,” (Cambridge University Press, Cambridge, 1993) Chap. 5, pp. 202–203.
- [4] H. Mehrer, *Diffusion in Solids: Fundamentals, Methods, Materials, Diffusion-Controlled Processes*,

Springer Series in Solid-State Sciences (Springer-Verlag Berlin Heidelberg, 2007).

- [5] A. Janotti, M. Krčmar, C. L. Fu, and R. C. Reed, Phys. Rev. Lett. **92**, 085901 (2004).
- [6] M. Mantina, Y. Wang, L. Q. Chen, Z. K. Liu, and C. Wolverton, Acta mater. **57**, 4102 (2009).
- [7] T. Garnier, Z. Li, M. Nastar, P. Bellon, and D. R. Trinkle, Phys. Rev. B **90**, 184301 (2014).
- [8] L. Onsager, Phys. Rev. **37**, 405 (1931).
- [9] L. Onsager, Ann. NY Acad. Sci. **46**, 241 (1945).
- [10] F. D. Fischer, J. Svoboda, and H. Petryk, Acta mater. **67**, 1 (2014).
- [11] G. E. Murch, in *Diffusion in Crystalline Solids*, edited by G. E. Murch and A. S. Nowick (Orlando, Florida: Academic Press, 1984) Chap. 7, pp. 379–427.
- [12] I. V. Belova and G. E. Murch, Philos. Mag. A **80**, 599 (2000).
- [13] I. V. Belova and G. E. Murch, Philos. Mag. A **81**, 1749 (2001).
- [14] I. V. Belova and G. E. Murch, Philos. Mag. **83**, 377 (2003).
- [15] I. V. Belova and G. E. Murch, Philos. Mag. **83**, 393 (2003).
- [16] M. Nastar, V. Y. Dobretsov, and G. Martin, Philos. Mag. A **80**, 155 (2000).
- [17] M. Nastar, Philos. Mag. **85**, 3767 (2005).
- [18] K. D. Belashchenko and V. G. Vaks, J. Phys. CM **10**, 1965 (1998).
- [19] V. G. Vaks, A. Y. Stroev, I. R. Pankratov, and A. D. Zabolotskiy, J. Exper. Theo. Phys. **119**, 272 (2014).
- [20] V. G. Vaks, K. Y. Khromov, I. R. Pankratov, and V. V. Popov, J. Exper. Theo. Phys. **150**, 69 (2016).
- [21] R. Kikuchi, Prog. Theor. Phys. Suppl. **35**, 1 (1966).
- [22] H. Sato and R. Kikuchi, Phys. Rev. B **28**, 648 (1983).
- [23] H. Sato, T. Ishikawa, and R. Kikuchi, J. Phys. Chem. Solids **46**, 1361 (1985).
- [24] E. W. Montroll and G. H. Weiss, J. Math. Phys. **6**, 167 (1965).
- [25] M. Koiwa and S. Ishioka, Philos. Mag. A **47**, 927 (1983).
- [26] D. R. Trinkle, Philos. Mag. **96**, 2714 (2016).
- [27] D. R. Trinkle, Philos. Mag. **97**, 2514 (2017).
- [28] Z. W. Gortel and M. A. Załuska-Kotur, Phys. Rev. B **70**, 125431 (2004).
- [29] M. A. Załuska-Kotur and Z. W. Gortel, Phys. Rev. B **76**, 245401 (2007).
- [30] M. A. Załuska-Kotur, Appl. Surf. Sci. **304**, 122 (2014).
- [31] The species can include vacancies as an independent chemical species.
- [32] See Supplemental Material at [http://link.aps.org/supplemental/](http://link.aps.org/supplemental/10.1103/Phys-) 10.1103/Phys-

RevLett.XXX.YYYYYY for detailed derivations of transport coefficients, their invariance, equivalence of kinetic Monte Carlo to the variational principle, and different approximation methods based on the variational principle.

- [33] R. Agarwal and D. R. Trinkle, *Acta mater.* **150**, 339 (2018).
- [34] A. R. Allnatt and A. B. Lidiard, *Rep. Prog. Phys.* **50**, 373 (1987).
- [35] A. D. Masi, P. A. Ferrari, S. Goldstein, and W. D. Wick, *J. Stat. Phys.* **55**, 787 (1989).
- [36] This is accomplished by subtracting a constant value from each \mathbf{y}_χ^α to ensure that the sums vanish. This constant leaves the mass transport vectors unchanged.
- [37] This follows as the correlated contribution is a symmetric negative semidefinite matrix, and the largest value possible is 0, which is achieved when the trace is similarly maximized.
- [38] H. Spohn, *Large Scale Dynamics of Interacting Particles* (Springer-Verlag Berlin Heidelberg, 1991).
- [39] C. Arita, P. L. Krapivsky, and K. Mallick, *Phys. Rev. E* **95**, 032121 (2017).
- [40] M. A. Novotny, *Phys. Rev. Lett.* **74**, 1 (1995).
- [41] B. Puchala, M. L. Falk, and K. Garikipati, *J. Chem. Phys.* **132**, 134104 (2010).
- [42] G. Nandipati, Y. Shim, and J. G. Amar, *Phys. Rev. B* **81**, 235415 (2010).
- [43] A. Chatterjee and A. F. Voter, *J. Chem. Phys.* **132**, 194101 (2010).
- [44] K. A. Fichthorn and Y. Lin, *J. Chem. Phys.* **138**, 164104 (2013).
- [45] L. K. Moleko, A. R. Allnatt, and E. L. Allnatt, *Philos. Mag. A* **59**, 141 (1989).
- [46] A. R. Allnatt, T. R. Paul, I. V. Belova, and G. E. Murch, *Philos. Mag.* **96**, 2969 (2016).
- [47] D. R. Trinkle, “ONSAGER,” <http://dallastrinkle.github.io/Onsager> (2017).
- [48] W. N. Bell, L. N. Olson, and J. B. Schroder, “PyAMG: Algebraic multigrid solvers in Python v3.0,” (2015), release 3.2.